


RUST-OLEUM®
INDUSTRIAL



DAC HYDRO ALU

Solar reflective and durable roof coating

- Prevents strong warming up of the surface
- Lasting 400% elastic layer without seams or joints
- Decorative aluminium finish resist UV-radiation, temperature changes, water and pollution
- Waterproof guarantee when used as topcoat on Dacfill®
- Water-based formulation, low odour

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

DAC HYDRO ALU

DESCRIPTION

Waterborne, ready-to-use aluminum coating for decoration, heat reflection and lasting protection of metal and most bituminous roofs.

RECOMMENDED USE

Decorative aluminium finish and durable protection of roofs with solar reflective characteristics. Builds an abrasion resistant rubberlike coat without joints or seams.

TECHNICAL DATA

Density (g/cm ³):	1,05
Gloss Level:	Metallic
Solids Content in weight:	51%
Solids content in volume:	48%
Water Vapour Permeability:	$\mu = 1836$

DRY TIMES BY 20° C/RH 50%

Touch dry:	4 hours
Dry to handle:	6-7 hours
Dry to recoat:	24 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

1000 micron (cons.: 1 m²/l)

RECOMMENDED DRY FILM THICKNESS

480 micron (cons.: 1 m²/l)

THEORETICAL CONSUMPTION

Waterproofing: 1 - 1,5 l/m² (depending on type of roof) as a second coat on Dacfill.
Esthetical: 0,3 - 0,5 l/m²

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrate must be clean, free from peeling, dust and dirt. Bridge cracks and fissures with Dacfill-mesh. Fill up joints with Elastofill. Very porous substrates have to be primed first with Primer 44HS. Dac-Hydro-Alu can be directly applied on metals (except new galvanised steel), roofing and most bituminous products (> 1 year). Dac-Hydro-Alu can be applied without any problem on most waterbased products like Dacfill and Noxyde. Do not apply directly on Fillcoat or Fillcoat Fibers. In this case it is necessary to apply first a coat of Dacfill. Dac-Hydro-Alu cannot be applied on flexible PVC, EPDM, tar or bituminous materials < 1 year, polyisobutylene and smooth bitumen-polymers. In case of stagnating water, Dac-Hydro-Alu must always be applied in combination with the Dacfill-mesh with a consumption of 2 l/m².

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Apply in drying conditions at minimum 5°C.

APPLICATION & THINNING: BRUSH

All types, do not dilute

APPLICATION & THINNING: ROLLER

Mohair roll with long hairs, do not dilute.

APPLICATION & THINNING: AIRLESS SPRAY

In case of airless-application, the aluminium finish will not be uniform; an airless-roll application is ideal, although in case of an airless application, it is necessary to roll over the surface with a roller.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended

CLEANING OF EQUIPMENT / SPILLS

Water

SAFETY DATA

VOC level:	70 g/l
VOC readymix:	70 g/l
VOC category:	A/i
VOC limit:	140 g/l
Grenelle:	Exterior
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 13/05/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu