



DAC HYDRO PRO

Rapid curing paint for Eternit® roof tiles

- Perfect adhesion on tiles, even difficult surfaces like fibre cement
- Resistant to UV radiation, acid rain, heat, frost and pollution
- Can be recoated after just 4 hours
- Flexible elastic paint does not crack or peel
- Long lasting gloss and colour retention

DAC HYDRO PRO

BESKRIVELSE

Rapid drying roof tile paint for fiber cement (Eternit®) tiles.

ANBEFALET BRUG

Renovates and protects in a durable way concrete roof tiles and fibre cement roofing slates.

ANBEFALET SYSTEM

Recommended primer per substrate:

- Concrete roofing tiles (normal porosity): No primer required
- Fibre cement (weathered and porous): Pegafix (see remarks)
- Fibre cement (dense, closed): No primer required
- Enamelled tiles: NOXYDE (25% diluted with water)

TEKNISK DATA

Tæthed:	1,18
Glansgrad:	Satin
Tørstofindhold i volumen:	42%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Håndteringstør:	2 hours (rain proof)
Genbehandlingstør:	4 hours
Fuldt hærdet:	1 week

ANBEFALET VÅDFILMTYKKELSE

1st coat: 85 µm (100 g/m²), 2nd coat: 70 µm (80 g/m²)

ANBEFALET TØRFILMTYKKELSE

1st coat: 36 µm, 2nd coat: 29 µm

TEORETISK FORBRUG

5 - 6 m²/l

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

High pressure cleaning (120 – 150 kg/cm²) if necessary in combination with AMW Fungicidal Wash for removal of moss and algae. All substrates have to be dry, clean and sound before applying the coating system.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Application temperature between 15 - 35°C, relative humidity max. 80%. Do not apply in full sun. Maximum surface temperature: 35°C.

PÅFØRING OG FORTYNDING: PENSEL

First coat dilute with 10-15% volume water; second coat dilute with maximum 5% volume water.

PÅFØRING OG FORTYNDING: RULLE

First coat dilute with 10-15% volume water; second coat dilute with maximum 5% volume water.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

First coat dilute with 10-15% volume water; second coat dilute with maximum 5% water. Nozzle: 015 / Pressure: 140 – 180 bars.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Not recommended

RENGØRING AF UDSTYR/SPILD

Water.

BEMÆRKNINGER

Apply in 2 coats to avoid local gloss differences. The surface must be dry, preferably no rain for 3 hours before applying the product. No dew or rain on the roof within 2 hours after application. Avoid spray applications when there are strong winds and provide cover for nearby substrates which do not need to be coated.

It is not recommended to apply Dac Hydro Pro on artificial slates of the Eternit type that are too strongly deteriorated. In order to verify, please check the mechanical stability of the surface after cleaning with a sharp knife or a screwdriver. If the fibres come loose, the surface can not be coated and needs to be renewed. It is recommended to always perform an adhesion test.

SIKKERHEDSDATA

VOC-niveau:	39 g/l
VOC-færdigblanding:	39 g/l
VOC-kategori:	A/i
VOC-grænse:	140 g/l
grenelle:	exterior
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 1 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 30°C.

Udstedelsesdato: 07/02/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu