

Quality Paints since 1845
MATHYS[®]



DURBOCEM[®]

Coating for humid inner and outer walls and cellars

- Builds a strong bond with the damp substrate
- Can be applied on chalking substrates
- Builds a strong bond with cement-based substrates
- Contains cement, and therefore this product is extremely suitable to be applied on damp substrates
- Can be recoated with Paracem[®] (when the substrate is dry)

WWW.MATHYSPAINTS.EU

BESKRIVELSE

A solvent-based paint based on plasticized acrylic resins for inside and outside use. It renews walls damaged by water and protects new walls against damp damage.

ANBEFALET BRUG

Painting of damp walls and cellars.

TEKNISK DATA

Tæthed:	1,24 - 1,28
Glansgrad:	Mat
Glansgrad ved 60°:	Matt: 2%
Faststofindhold i vægt:	61 - 63 %
Tørstofindhold i volumen:	28 - 40 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	2 hours
Håndteringstør:	2 hours
Genbehandlingstør:	24 hours
Fuldt hærdet:	24 hours

ANBEFALET VÅDFILM TYKKELSE

500 µm

ANBEFALET TØRFILM TYKKELSE

200 µm

TEORETISK FORBRUG

1,5 - 3 m²/l (total consumption, 2 coats)

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Brush off chalking surfaces with a wire brush. Water infiltration leaks must be made watertight with special quick cement by using a hawk or trowel. Let it harden.

BRUGSANVISNING

To ensure homogeneity, coating material should be thoroughly stirred prior to use.

ANVENDELSBETINGELSER

Work in a well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Use a semi-hard brush. Do not dilute.

PÅFØRING OG FORTYNDING: RULLE

Use a mohair roller. Do not dilute.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Not recommended.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Not recommended.

RENGØRING AF Udstyr/SPILD

White spirit.

BEMÆRKNINGER

- 1st coat: impregnate substrate using a semi-brush; walls in bad condition must be treated saturation. 2nd coat: finish after 24 hours with brush
- Since it concerns specific applications (e.g. caves), there has to be excellent ventilation, during the first weeks after application.
- Durbocem does not stop saltpetre efflorescence, does not resist against underground water pressure and therefore it cannot be considered as a waterproofing product.

SIKKERHEDSDATA

VOC-niveau:	500 g/L
VOC-færdigblanding:	500 g/l
VOC-kategori:	A/i
VOC-grænse:	500 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 12/07/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu