

Quality Paints since 1845
MATHYS®



ELASTOFILL®

Elastic jointing paste based on acrylic dispersions

- Forms a rubberlike mass with permanently high elasticity (> 900%) after evaporation of the water
- Can absorb strong expansions and deformations
- Alkali resistant
- Very resistant to ageing
- Waterproof

ОПИСАНИЕ

An elastic, paintable jointing paste based on acrylic dispersions for sealing, jointing, filling. For inside use.

ПРЕПОРЪЧАНА УПОТРЕБА

Sealing, jointing, filling, glueing on concrete, wood, metal, glass, hard PVC, tiles, plaster, alu-bitumen, etc.

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 3 hours, film thickness 8 mm
Сух за употреба: 8 hours, film thickness 8 mm
Готов за повторно нанасяне: 1 day, film thickness 8 mm
Напълно втвърден: ± 1 week, film thickness 8 mm

РАЗХОДНА НОРМА

For a joint of 10 mm wide and 15 mm deep: ± 6 meters run.
Jointing paste has to be applied in maximum 10 mm wet film thickness.

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

Grind out fine cracks in V-shape till about 0,5 cm wide; if depth > 1/2 x width, apply a back filling. The crack edges must be primed with Parafix, Pegafix or Vernac (diluted with Thinner 22). Hard PVC is to be primed with Primer 44 HS, metal and glass with diluted Noxyde.

НАЧИН НА УПОТРЕБА

Manual spray gun (nozzle free to choose) - spatula, palette knife, glue spreader (combed lime rills ± 3 mm thick).

УСЛОВИЯ ЗА НАНАСЯНЕ

> 5°C, Max. R.H. 80%

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water. After drying Elastofill can only be removed mechanically or softened with a synthetic thinner; then remove by rubbing or scratching.

ЗАБЕЛЕЖКИ

Joints have to be smoothened with a finger or with a cloth soaked in Thinner 22 or in water (+ soap).

The surface in contact with the air must be sufficiently large, since Elastofill is to be transformed into a rubber like mass by evaporation of the water.

On porous surfaces, always use an appropriate primer.

Elastofill can be recoated with the following paints: acrylic paints Murfill, Paracem (Elastofill has to be isolated first with Porisol), Paracem Semi-Gloss, Pegacryl, Pegacryl Satin, with high and satin gloss alkyd enamels, with Porisol and Pegatex.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ограничение за ЛОС: 5 g/l
Забележки относно безопасността: Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Дата на издаване: 14/04/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, да да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu