



ELASTOPRO

Plasto-elastic sealant for inside and outside use

- For inside and outside use
- Sealing and finishing of joints and cracks
- Quick paintable
- Shrinks hardly
- Excellent adhesion

ELASTOPRO

BESKRIVELSE

ElastoPro is based on an acrylic dispersion. The product is suitable for sealing connecting joints, cracks and joints.

ANBEFALET BRUG

Connecting joints between frames and masonry, stucco and gypsum board with moderate movement. Repairing and sealing cracks and joints in cellular concrete, stone plaster and wood. Not suitable for dilatation cracks.

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Genbehandlingstør:	After skin formation (> 20 minutes)
Fuldt hærdet:	1 to 2 weeks, depending on temperature, air humidity and joint width.

TEORETISK FORBRUG

± 12 running meters for a joint of 5 x 5 mm.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surface must be clean, dust and oil-free. It is advisable to prime sensitive and mineral substrates in order to achieve a better adhesion.

BRUGSANVISNING

Joint building:

Fix joints with PE or PU to the correct depth.

Minimum joint width: 5 mm, maximum joint width 25 mm.

To prevent damage use only blunt and smooth spatulas. In case of joints with a rigid substrate use a polyethylene film to prevent three-point attachment.

Unsuitable are joints containing oil, tar, bitumen, natural rubber, EPDM or Chloroprene.

Joint finishing:

In order to achieve a smooth optical finish we advise to tape the edges with a suitable tape.

Apply ElastoPro without air confined in the joint. Completely fill the joint. Remove all unnecessary kit with a suitable spatula. Finish the joint by spraying a little water on the joint (add no smoothing additive to the water). To prevent damage later on, remove the tape around the edges.

ANVENDELSESBETINGELSER

Application temperature +5°C to +25°C.

Protect ElastoPro during the curing process against frost.

Low temperatures will slow down the curing process.

RENGØRING AF UDSTYR/SPILD

Water. After drying ElastoPro can only be removed mechanically.

BEMÆRKNINGER

ElastoPro is recoatable with dispersion and alkyd coatings (testing before application is advisable). In case of static joints with small movement (max. 5%) ElastoPro can be coated after complete hardening. Recoating with high filled dispersion coats can give cracking in the layer.

ElastoPro is not suitable for seals between glass, glazed surfaces and joints with standing water.

ElastoPro is available in 310 ml cartridges.

HOLDBARHED

Minimum of 12 months from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 07/02/2025

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
36, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zellem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu