



**FAIRTEX®**

## Matt paint for interior walls and ceilings

- Smooth and completely splash-free roller application
- Covers on porous and non porous substrates in 2 coats without gloss differences
- Uniform matt finish without turning
- Odorless
- High whiteness

## DESCRIPTION

Matt acrylic paint for interior walls and ceilings and can be applied on most surfaces.

## RECOMMENDED USE

Inner decoration on most common substrates such as plaster, bricks and concrete. Also old paint coats in good condition and most wallpaper can be recoated with Fairtex

## TECHNICAL DATA

Density (g/cm³):	1,38 - 1,41
Gloss Level:	Matt
Gloss level at 85°:	1-2%
Solids Content in weight:	48 - 51 %
Solids content in volume:	28 - 32 %
Wet Scrub Resistance (EN 13300):	Class 2 (≥ 5 µm and <20 µm at 200 strokes)

## DRY TIMES BY 20° C/RH 50%

Touch dry:	30 minutes
Dry to handle:	Not applicable
Dry to recoat:	3 hours
Fully cured:	1 week

## RECOMMENDED WET FILM THICKNESS

140 µm

## RECOMMENDED DRY FILM THICKNESS

45 µm

## THEORETICAL CONSUMPTION

6 - 8 m²/l

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

Always work on a dry stable substrate. On porous substrates, no specific pre-treatment is required in most cases. Slightly chalking substrates or new plaster should first be impregnated with Pegafix or, for very fast recoating on all substrates, with Zinsser primers Bulls Eye 123 or 123 Plus. Water or nicotine stains should be isolated with Pegamat RL or Pegamat Aqua Isole, or with Zinsser primers Bulls Eye 123, 123 Plus, or B-I-N.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply at a temperature of minimum 5°C and a R.H. of max. 80%

## APPLICATION & THINNING: BRUSH

Apply undiluted

## APPLICATION & THINNING: ROLLER

Apply undiluted

## APPLICATION & THINNING: AIRLESS SPRAY

If necessary, dilute with 2-5% volume of water. Nozzle : 016-018 / Pressure 200 bars.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended

## CLEANING OF EQUIPMENT / SPILLS

Water

## SAFETY DATA

VOC readymix:	30 g/l
VOC category:	A/a
VOC limit:	30 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans. If stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35 C.

Date issued: 07/02/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)