

Quality Paints since 1845
MATHYS®



FASSICOAT®

Single paint system

- Moisture-regulating paint
- Serves at the same time as primer, surfacer and finish
- Excellent weather resistance

FASSICOAT®

DESCRIPTION

Satin gloss single paint system based on alkyd resins for woodwork.

RECOMMENDED USE

Painting of woodwork.

RECOMMENDED SYSTEM

Serves at the same time as primer, surfacer and finish - moisture-regulating paint - excellent weather resistance.

TECHNICAL DATA

Density (g/cm³):	1,33 - 1,38
Gloss Level:	Satin
Solids Content in weight:	69 - 73 %
Solids content in volume:	51 - 56 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	3 - 4 hours
Dry to handle:	5 hours
Dry to recoat:	24 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

100 µm

RECOMMENDED DRY FILM THICKNESS

55 µm

THEORETICAL CONSUMPTION

10 - 15 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Fassicoat serves as primer, surfacer and finish. Therefore, it is not necessary to use a special primer. In case of application on new and non-treated wood, if necessary, dilute the first coat with ± 3% volume of white spirit. In case of jointing, use Plastopan Super or Pegaflex by preference.

Poor quality wood: user primer FassiForce. Do not apply Fassicoat directly on metallic substrates; in such situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity max. 80%

APPLICATION & THINNING: BRUSH

By preference, apply undiluted with flat brush.

APPLICATION & THINNING: ROLLER

By preference, apply undiluted with flat brush.

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 015 / Pressure: 180 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Possible with maximum 3% volume White Spirit.

CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22

REMARKS

May be applied on slightly damp wood (< 20%).

SAFETY DATA

VOC category:	A/d
VOC limit:	300 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu