

Quality Paints since 1845
MATHYS[®]



FASSICOAT[®]

Single paint system

- Moisture-regulating paint
- Serves at the same time as primer, surfacer and finish
- Excellent weather resistance

FASSICOAT®

BESKRIVELSE

Satin gloss single paint system based on alkyd resins for woodwork.

ANBEFALT BRUK

Painting of woodwork.

ANBEFALT SYSTEM

Serves at the same time as primer, surfacer and finish - moisture-regulating paint - excellent weather resistance.

TEKNISKE DATA

Tetthet:	1,33 - 1,38
Glansgrad:	Satinert
Tørrstoffinnhold i vekt:	69 - 73 %
Tørrstoffinnhold i volum:	51 - 56 %

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	3 - 4 hours
Håndterbar:	5 hours
Overmalbar:	24 hours
Herdetid:	1 week

ANBEFALT VÅTFILMYKKELSE

100 µm

ANBEFALT TØRRFILMYKKELSE

55 µm

TEORETISK FORBRUK

10 - 15 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Fassicoat serves as primer, surfacer and finish. Therefore, it is not necessary to use a special primer. In case of application on new and non-treated wood, if necessary, dilute the first coat with ± 3% volume of white spirit. In case of jointing, use Plastopan Super or Pegaflex by preference.

Poor quality wood: user primer FassiForce. Do not apply Fassicoat directly on metallic substrates; in such situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity max. 80%

PÅFØRING & FORTYNNING: PENSEL

By preference, apply undiluted with flat brush.

PÅFØRING & FORTYNNING: RULLE

By preference, apply undiluted with flat brush.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 015 / Pressure: 180 bars.

PÅFØRING & FORTYNNING: FORSTØVNINGSSPRØYTE

Possible with maximum 3% volume White Spirit.

RENGJØRING AV UTSTYR/SPILL

White spirit or Thinner 22

MERKNADER

May be applied on slightly damp wood (< 20%).

SIKKERHETSDATA

VOC kategori:	A/d
VOC grense:	300 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu