



FASSICRYL MATT

Water-based scratch-resistant matt lacquer

- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention
- Easy to apply with a brush and a roller



FASSICRYL MATT

BESKRIVELSE

Fassicryl Matt is a top-quality water-based matt indoor lacquer based on PU acrylate. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt is scratch-resistant and skin grease-resistant. The paint has excellent flow viscosity and good colour and gloss retention.

ANBEFALET BRUG

This water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

ANBEFALET SYSTEM

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TEKNISK DATA

Tæthed:	1,23 (white - wit - blanc - weiß)
Glansgrad:	Mat
Glansgrad ved 60°:	5-10%
Tørstofindhold i volumen:	37% (white - wit - blanc - weiß)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Genbehandlingstør:	6 hours

ANBEFALET VÅDFILMTYKKELSE

67 µm (white - wit - blanc - weiß)

ANBEFALET TØRFILMTYKKELSE

25 µm (white - wit - blanc - weiß)

TEORETISK FORBRUG

15 m²/l/coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

BRUGSANVISNING

To ensure homogeneity, thoroughly stir prior to use.

ANVENDELSESBETINGELSER

> 8°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Apply undiluted with brush with synthetic bristles.

PÅFØRING OG FORTYNDING: RULLE

Apply undiluted with a 10 mm micro fiber roller.

RENGØRING AF UDSTYR/SPILD

Clean the material with water and dispose of the residue appropriately.

BEMÆRKNINGER

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

SIKKERHEDSDATA

VOC-niveau:	40g/l
VOC-færdigblanding:	40g/l
VOC-kategori:	IIA/d
VOC-grænse:	130g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 30/09/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu