

Quality Paints since 1845
MATHYS[®]



FASSICRYL MATT

Water-based scratch-resistant matt lacquer

- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention
- Easy to apply with a brush and a roller



FASSICRYL MATT

BESKRIVELSE

Fassicryl Matt is a top-quality water-based matt indoor lacquer based on PU acrylate. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt is scratch-resistant and skin grease-resistant. The paint has excellent flow viscosity and good colour and gloss retention.

ANBEFALT BRUK

This water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

ANBEFALT SYSTEM

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TEKNISKE DATA

Tetthet:	1,23 (white - wit - blanc - weiß)
Glansgrad:	Matt
Glansgrad ved 60°:	5-10%
Tørrestoffinnhold i volum:	37% (white - wit - blanc - weiß)

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støvtørr:	1 hour
Overmalbar:	6 hours

ANBEFALT VÅTFILMTYKKELSE

67 µm (white - wit - blanc - weiß)

ANBEFALT TØRRFILMTYKKELSE

25 µm (white - wit - blanc - weiß)

TEORETISK FORBRUK

15 m²/l/coat

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

BRUKSANVISNING

To ensure homogeneity, thoroughly stir prior to use.

PÅFØRINGSBETINGELSER

> 8°C, < 80% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply undiluted with brush with synthetic bristles.

PÅFØRING & FORTYNNING: RULLE

Apply undiluted with a 10 mm micro fiber roller.

RENGJØRING AV UTSTYR/SPILL

Clean the material with water and dispose of the residue appropriately.

MERKNADER

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

SIKKERHETSDATA

VOC nivå:	40g/l
VOC ferdigblandet:	40g/l
VOC kategori:	IIA/d
VOC grense:	130g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstillende Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu