



FASSICRYL MATT SPRAY

Sprayable water-based matt lacquer

- Sprayable (airless and airmix)
- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention



FASSICRYL MATT SPRAY

ОПИСАНИЕ

Fassicryl Matt Spray is a top-quality sprayable water-based matt indoor lacquer based on PU acrylate with excellent coverage. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Matt Spray is scratch-resistant and skin grease-resistant. The paint is slightly thixotropic, has excellent flow viscosity and good colour and gloss retention. Can be applied with a brush.

ПРЕПОРЪЧАНА УПОТРЕБА

This sprayable water-based scratch-free matt lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,20 (white - wit - blanc - weiß)
Гланцово ниво:	Мат
Гланцово ниво при 60°:	5-10%
Съдържание на твърди вещества в обема:	35% (white - wit - blanc - weiß)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1 hour
Готов за повторно нанасяне:	6 hours

МОКЪР СЛОЙ

150-250 µm

РАЗХОДНА НОРМА

4-6 m²/l/coat

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.

New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.

Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, thoroughly stir prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

> 8°C, < 80% R.H.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

This sprayable paint can also be applied with a brush. Apply undiluted with brush with synthetic bristles.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Nozzle: 0.009 - 0.012 / Pressure: Ca. 70 bars

The product is ready for use; do not dilute.

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Air-assist - Nozzle: 0.009 - 0.012 / Pressure: Ca. 60 bars / Air pressure: Ca.2 bars

The product is ready for use; do not dilute.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Clean the material with water and dispose of the residue appropriately.

ЗАБЕЛЕЖКИ

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

Scratch-resistance is achieved after 15-30 days depending on the colour.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	35g/l
Готов за употреба ЛОС (VOC Readymix):	35g/l
Категория ЛОС:	IIA/d
Ограничение за ЛОС:	130g/l
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Дата на издаване: 23/06/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu