Quality Paints since 1845
MATHYS®

FASSICRYL SATIN SPRAY

Sprayable water-based silky gloss lacquer

- Sprayable (airless and airmix)
- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention

FASSICRYL SATIN SPRAY

BESKRIVELSE
Fassicryl Satin Spray is a top-quality sprayable water-based silky gloss indoor lacquer based on PU acrylate with excellent coverage. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Satin Spray is scratch-resistant and skin grease-resistant. The paint is slightly thixotropic, has excellent flow viscosity and good colour and gloss retention. Can be applied with a brush.

ANBEFALET BRUG
This sprayable water-based scratch-free silky gloss lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

ANBEFALET SYSTEM
Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TEKNISK DATA

Tæthed:	1,20 (white - wit - blanc - weiß)
Glansgrad:	Satin
Glansgrad ved 60°:	45-50% (white - wit - blanc - weiß)
Tørstofindhold i volumen:	35% (white - wit - blanc - weiß)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Genbehandlingstør:	6 hours

ANBEFALET VÅDFILMTYKKELSE
150-250 µm

TEORETISK FORBRUG
4-6 m²/l/coat

PRAKTISK FORBRUG
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN
The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.
New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.
Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

BRUGSANVISNING
To ensure homogeneity, thoroughly stir prior to use.

ANVENDELSESBETINGELSER
> 8°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL
This sprayable paint can also be applied with a brush. Apply undiluted with brush with synthetic bristles.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE
Nozzle: 0.009 - 0.012 / Pressure: Ca. 70 bars
The product is ready for use; do not dilute.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE
Air-assist - Nozzle: 0.009 - 0.012 / Pressure: Ca. 60 bars / Air pressure: Ca.2 bars
The product is ready for use; do not dilute.

RENGØRING AF UDSTYR/SPILD
Clean the material with water and dispose of the residue appropriately.

BEMÆRKNINGER
Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.
Scratch-resistance is achieved after 15-30 days depending on the colour.

SIKKERHEDSDATA

VOC-niveau:	30g/l
VOC-færdigblanding:	30g/l
VOC-kategori:	IIA/d
VOC-grænse:	130g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 28/05/2026

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu