Quality Paints since 1845
MATHYS®

FASSICRYL SATIN SPRAY

Sprayable water-based silky gloss lacquer

- Sprayable (airless and airmix)
- Skin grease-resistant
- Scratch-resistance and easy to clean
- Excellent flow viscosity
- Good colour and gloss retention

FASSICRYL SATIN SPRAY

BESKRIVNING
Fassicryl Satin Spray is a top-quality sprayable water-based silky gloss indoor lacquer based on PU acrylate with excellent coverage. Suitable as a top layer to cover wood as well as any pre-treated surface such as plastic or metal. Fassicryl Satin Spray is scratch-resistant and skin grease-resistant. The paint is slightly thixotropic, has excellent flow viscosity and good colour and gloss retention. Can be applied with a brush.

REKOMMENDERAD ANVÄNDNING
This sprayable water-based scratch-free silky gloss lacquer is suitable as a top layer to cover wood as well as any properly pre-treated surface such as plastic or metal.

REKOMMENDERAT SYSTEM
Priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TEKNISK DATA

Densitet:	1,20 (white - wit - blanc - weiß)
Glansnivå:	Satin
Glansnivå vid 60°:	45-50% (white - wit - blanc - weiß)
Torrsubstansvolym:	35% (white - wit - blanc - weiß)

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1 hour
Torktid:	6 hours

REKOMMENDERAD VÅTFILMSTJOCKLEK
150-250 µm

ÅTGÅNG
4-6 m²/l/coat

ÅTGÅNG INFORMATION
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FÖRBEREDELSER
The surface must be dry and free of dust and grease. Round off sharp edges so that you can apply a good coating.
New work: priming with Fassicryl Primer. Use Fassicryl Sealing Primer on bleeding wood types.
Existing work: lightly sand old and properly adhesive coats. Remove loose, cracked or flaky coats. Treat exposed locations as new wood.

APPLICERING
To ensure homogeneity, thoroughly stir prior to use.

APPLICERINGSFÖRHÅLLANDEN
> 8°C, < 80% R.H.

REDSKAP
This sprayable paint can also be applied with a brush. Apply undiluted with brush with synthetic bristles.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA
Nozzle: 0.009 - 0.012 / Pressure: Ca. 70 bars
The product is ready for use; do not dilute.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA
Air-assist - Nozzle: 0.009 - 0.012 / Pressure: Ca. 60 bars / Air pressure: Ca.2 bars
The product is ready for use; do not dilute.

RENGÖRING AV REDSKAP/SPILL
Clean the material with water and dispose of the residue appropriately.

INFORMATION
Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.
Scratch-resistance is achieved after 15-30 days depending on the colour.

SÄKERHETSDATA

VOC-nivå:	30g/l
VOC färdigmix:	30g/l
VOC-kategori:	IIA/d
VOC-gräns:	130g/l
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Utgivningsdatum: 22/06/2026

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdskador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu