

Quality Paints since 1845  
**MATHYS**<sup>®</sup>



## FASSICRYL SEALING PRIMER

### Water-based insulating primer

- Insulating primer
- Covers bleeding knots and resin streaks
- Superb adhesion
- Perfect flow viscosity



# FASSICRYL SEALING PRIMER

## BESKRIVELSE

Fassicryl Sealing Primer is a water-based primer based on an acrylic dispersion with insulating properties for bleeding wood types, for indoor and outdoor use. Fast-drying adhesive primer with perfect flow viscosity. Suitable as a primer for various wood types and properly cleaned paint layers with good adhesion. Can also be applied to plastic and non-ferrous metals.

## ANBEFALET BRUG

Water-based insulating primer for various types of (hard) wood. Covers bleeding knots and resin streaks.

## ANBEFALET SYSTEM

Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

## TEKNISK DATA

Tæthed: 1,35 (white - wit - blanc - weiß)  
Glansgrad: Mat  
Tørstofindhold i volumen: 38% (white - wit - blanc - weiß)

## TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør: 1 hour  
Genbehandlingstør: 6 hours - in the case of bleeding wood types, repaintable after 16 hours.

## ANBEFALET VÅDFILM TYKKELSE

80 µm (white - wit - blanc - weiß)

## ANBEFALET TØRFILM TYKKELSE

30 µm (white - wit - blanc - weiß)

## TEORETISK FORBRUG

12-14 m<sup>2</sup>/l/coat

## PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FORBEHANDLING AF OVERFLADEN

The surface must be dry and free of dust and grease.  
Aged wood: remove until the healthy wood is exposed.  
Exposed wood: degrease (Multi Cleaner), sand and remove all dust.  
Old paint layers in a poor condition: strip (NR.1 GREEN PAINT STRIPPER), degrease (Multi Cleaner), sand, remove all dust and prime.  
Old paint layers in a good condition: degrease (Multi Cleaner), sand and remove all dust.  
Round off sharp edges so that you can apply a good coating.

## BRUGSANVISNING

The product must be firmly stirred into a homogeneous substance prior to its use. Use a suitable brush or roller to apply one or two coats.

## ANVENDELSBETINGELSER

> 8°C, < 80% R.H.

## PÅFØRING OG FORTYNDING: PENSEL

Apply undiluted with brush with synthetic bristles.

## PÅFØRING OG FORTYNDING: RULLE

Apply undiluted with a 10 mm micro fiber roller.

## RENGØRING AF UDS TYR/SPILD

Clean the material with water and dispose of the residue appropriately.

## BEMÆRKNINGER

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

## SIKKERHEDSDATA

VOC-niveau: 16g/l  
VOC-færdigblanding: 16g/l  
VOC-kategori: IIA/d  
VOC-grænse: 130g/l  
Bemærkninger om sikkerhed: Consult Safety Data Sheet and Safety Information printed on the can.

## HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 03/05/2024

**Tilgængelige farver og pakningsstørrelser:** Der henvises til den respektive produktside på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

**Ansvarsfraskrivelse:** Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu) eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu