FASSICRYL SEALING PRIMER

Water-based insulating primer

- Insulating primer
- Covers bleeding knots and resin streaks
- Superb adhesion
- Perfect flow viscosity

FASSICRYL SEALING PRIMER

BESKRIVELSE
Fassicryl Sealing Primer is a water-based primer based on an acrylic dispersion with insulating properties for bleeding wood types, for indoor and outdoor use. Fast-drying adhesive primer with perfect flow viscosity. Suitable as a primer for various wood types and properly cleaned paint layers with good adhesion. Can also be applied to plastic and non-ferrous metals.

ANBEFALET BRUG
Water-based insulating primer for various types of (hard) wood. Covers bleeding knots and resin streaks.

ANBEFALET SYSTEM
Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TEKNISK DATA

Tæthed:	1,35 (white - wit - blanc - weiß)
Glansgrad:	Mat
Tørstofindhold i volumen:	38% (white - wit - blanc - weiß)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Genbehandlingstør:	6 hours - in the case of bleeding wood types, repaintable after 16 hours.

ANBEFALET VÅDFILMTYKKELSE
80 µm (white - wit - blanc - weiß)

ANBEFALET TØRFILMTYKKELSE
30 µm (white - wit - blanc - weiß)

TEORETISK FORBRUG
12-14 m²/l/coat

PRAKTISK FORBRUG
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN
The surface must be dry and free of dust and grease.
Aged wood: remove until the healthy wood is exposed.
Exposed wood: degrease (Multi Cleaner), sand and remove all dust.
Old paint layers in a poor condition: strip (NR.1 GREEN PAINT STRIPPER), degrease (Multi Cleaner), sand, remove all dust and prime.
Old paint layers in a good condition: degrease (Multi Cleaner), sand and remove all dust.
Round off sharp edges so that you can apply a good coating.

BRUGSANVISNING
The product must be firmly stirred into a homogeneous substance prior to its use. Use a suitable brush or roller to apply one or two coats.

ANVENDELSESBETINGELSER
> 8°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL
Apply undiluted with brush with synthetic bristles.

PÅFØRING OG FORTYNDING: RULLE
Apply undiluted with a 10 mm micro fiber roller.

RENGØRING AF UDSTYR/SPILD
Clean the material with water and dispose of the residue appropriately.

BEMÆRKNINGER
Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

SIKKERHEDSDATA

VOC-niveau:	16g/l
VOC-færdigblanding:	16g/l
VOC-kategori:	IIA/d
VOC-grænse:	130g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 06/02/2023

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu