



FASSICRYL SEALING PRIMER

Water-based insulating primer

- Insulating primer
- Covers bleeding knots and resin streaks
- Superb adhesion
- Perfect flow viscosity



FASSICRYL SEALING PRIMER

DESCRIPTION

Fassicryl Sealing Primer is a water-based primer based on an acrylic dispersion with insulating properties for bleeding wood types, for indoor and outdoor use. Fast-drying adhesive primer with perfect flow viscosity. Suitable as a primer for various wood types and properly cleaned paint layers with good adhesion. Can also be applied to plastic and non-ferrous metals.

RECOMMENDED USE

Water-based insulating primer for various types of (hard) wood. Covers bleeding knots and resin streaks.

RECOMMENDED SYSTEM

Use Fassicryl Sealing Primer on bleeding wood types. Finish with a Fassicryl lacquer.

TECHNICAL DATA

Density (g/cm³):	1,35 (white - wit - blanc - weiß)
Gloss Level:	Matt
Solids content in volume:	38% (white - wit - blanc - weiß)

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to recoat:	6 hours - in the case of bleeding wood types, repaintable after 16 hours.

RECOMMENDED WET FILM THICKNESS

80 µm (white - wit - blanc - weiß)

RECOMMENDED DRY FILM THICKNESS

30 µm (white - wit - blanc - weiß)

THEORETICAL CONSUMPTION

12-14 m²/l/coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The surface must be dry and free of dust and grease.
Aged wood: remove until the healthy wood is exposed.
Exposed wood: degrease (Multi Cleaner), sand and remove all dust.
Old paint layers in a poor condition: strip (NR.1 GREEN PAINT STRIPPER), degrease (Multi Cleaner), sand, remove all dust and prime.
Old paint layers in a good condition: degrease (Multi Cleaner), sand and remove all dust.
Round off sharp edges so that you can apply a good coating.

DIRECTIONS FOR USE

The product must be firmly stirred into a homogeneous substance prior to its use. Use a suitable brush or roller to apply one or two coats.

APPLICATION CONDITIONS

> 8°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Apply undiluted with brush with synthetic bristles.

APPLICATION & THINNING: ROLLER

Apply undiluted with a 10 mm micro fiber roller.

CLEANING OF EQUIPMENT / SPILLS

Clean the material with water and dispose of the residue appropriately.

REMARKS

Do not apply paint at temperatures below 8°C. The surface temperature must be at least 3°C above the dew point.

SAFETY DATA

VOC level:	16g/l
VOC readymix:	16g/l
VOC category:	IIA/d
VOC limit:	130g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu