



Quality Paints since 1845
MATHYS[®]



FASSIFORCE[®]

Wood impregnation

- Strengthens the wood structure
- Improves adhesion of paint



FASSIFORCE®

BESKRIVELSE

This impregnating agent for wood is based on a phenolic resin and Chinese wood oil blend. Strengthens and durably protects untreated or stripped wood.

ANBEFALET BRUG

Impregnation of new exterior wood that is not of first quality or bare exterior wood that is damaged in some way.

TEKNISK DATA

Tæthed:	0,85 - 0,87
Glansgrad ved 60°:	Glossy, after saturation of the wood: ± 90%
Faststofindhold i vægt:	± 35 %
Tørstofindhold i volumen:	± 28 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	2,5 hours
Håndteringstør:	3 hours
Genbehandlingstør:	24 hours
Fuldt hærdet:	± 1 week

ANBEFALET VÅDFILMTYKKELSE

100 µm

ANBEFALET TØRFILMTYKKELSE

28 µm

TEORETISK FORBRUG

± 10 m²/l

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Remove old traces of paint or varnish either by scraping or thermal or chemical removal (Rapid Super). The wood must be dry sanded, degreased and made dust free, if necessary, followed by a coat of FassiForce. On some very damaged porous wood parts a second coat may be necessary.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

All types. If necessary dilute with white spirit.

PÅFØRING OG FORTYNDING: RULLE

Not recommended.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Not recommended.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Yes, do not dilute.

RENGØRING AF UDSTYR/SPILD

White spirit.

SIKKERHEDSDATA

VOC-niveau:	555 g/l
VOC-færdigblanding:	555 g/l
VOC-kategori:	A/h
VOC-grænse:	750 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 29/11/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu