



FASSIFORCE®

Wood impregnation

- Strengthens the wood structure
- Improves adhesion of paint

FASSIFORCE®

DESCRIPTION

This impregnating agent for wood is based on a phenolic resin and Chinese wood oil blend. Strengthens and durably protects untreated or stripped wood.

RECOMMENDED USE

Impregnation of new exterior wood that is not of first quality or bare exterior wood that is damaged in some way.

TECHNICAL DATA

| | |
|---------------------------|---|
| Density (g/cm³): | 0,85 - 0,87 |
| Gloss level at 60°: | Glossy, after saturation of the wood: ± 90% |
| Solids Content in weight: | ± 35 % |
| Solids content in volume: | ± 28 % |

DRY TIMES BY 20° C/RH 50%

| | |
|----------------|-----------|
| Touch dry: | 2,5 hours |
| Dry to handle: | 3 hours |
| Dry to recoat: | 24 hours |
| Fully cured: | ± 1 week |

RECOMMENDED WET FILM THICKNESS

100 µm

RECOMMENDED DRY FILM THICKNESS

28 µm

THEORETICAL CONSUMPTION

± 10 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Remove old traces of paint or varnish either by scraping or thermal or chemical removal (Rapid Super). The wood must be dry sanded, degreased and made dust free, if necessary, followed by a coat of FassiForce. On some very damaged porous wood parts a second coat may be necessary.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

All types. If necessary dilute with white spirit.

APPLICATION & THINNING: ROLLER

Not recommended.

APPLICATION & THINNING: AIRLESS SPRAY

Not recommended.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Yes, do not dilute.

CLEANING OF EQUIPMENT / SPILLS

White spirit.

SAFETY DATA

| | |
|---------------------------|--|
| VOC level: | 555 g/l |
| VOC readymix: | 555 g/l |
| VOC category: | A/h |
| VOC limit: | 750 g/l |
| Remarks regarding safety: | Consult Safety Data Sheet and Safety Information printed on the can. |

SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu