



FASSILUX® AQUA XPE SATIN

Water dilutable air-drying satin topcoat

- Can be used in- and exterior
- Quick drying
- Low in odour and VOC,
- Easy to apply
- Excellent flow and levelling characteristics



FASSILUX® AQUA XPE SATIN

DESCRIPTION

Waterbased satin gloss PU/ Alkyd topcoat for indoor and outdoor works

RECOMMENDED USE

As scratch resistant satin finish on properly prepared wooden, or other already painted mineral substrates.

TECHNICAL DATA

Density (g/cm³):	1,4
Gloss Level:	Satin
Gloss level at 60°:	30 - 35%
Solids Content in weight:	57%
Solids content in volume:	39%

DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours
Dry to handle:	24 hours
Dry to recoat:	24 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

80 µm

RECOMMENDED DRY FILM THICKNESS

30 µm

THEORETICAL CONSUMPTION

Approx. 12 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

- New work: the substrate needs to be clean, dry and free of fats and oils. The substrate has to be primed with Fassiprim Aqua.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.
- Block wood knots and sap streaks with Zinsser primer B-I-N.
- Interior: for stain, graffiti, tannin and other substances bleed blocking, and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus.
- Exterior: block tannin or other typical bleeding substances from redwoods etc, block graffiti, and/or for very fast recoating, use with Zinsser primer Cover-Stain.
-

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dew point.

APPLICATION & THINNING: BRUSH

Dilute, if necessary, up to maximum 5% volume with water.

APPLICATION & THINNING: ROLLER

Dilute, if necessary, up to maximum 5% volume with water.

APPLICATION & THINNING: AIRLESS SPRAY

- Nozzle: 0,011 - 0,013 inch / Pressure: 120 bars.
- Thinning 3% volume water.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

- Nozzle 1.5 - 2.0 mm / Pressure: 2 - 3 bars.
- Thinning 10 - 15% volume water.

CLEANING OF EQUIPMENT / SPILLS

Warm water.

REMARKS

If conventional spraying is used, the gloss might be somewhat lower.

SAFETY DATA

VOC level:	12 g/l max.
VOC category:	A/d
VOC limit:	130 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 1 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 23/06/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu