



FASSILUX[®] GLOSS

Solvent based high gloss enamel

- Simple and fast application
- Excellent flow
- Excellent scratch and wear resistance
- Good outdoor durability, weatherproof
- Quick drying

FASSILUX® GLOSS

BESKRIVELSE

Solvent based high gloss enamel based on alkylid resins.

ANBEFALET BRUG

Topcoat for interior and exterior woodwork.

ANBEFALET SYSTEM

TEKNISK DATA

Tæthed:	1,17 - 1,20
Glansgrad:	Blank
Faststofindhold i vægt:	77 - 79 %
Tørstofindhold i volumen:	70 - 72 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	3 hours
Håndteringstør:	4 hours
Genbehandlingstør:	24 hours
Fuldt hærdet:	1 week

ANBEFALET VÅDFILMTYKKELSE

50 µm

ANBEFALET TØRFILMTYKKELSE

35 µm

TEORETISK FORBRUG

20 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

For top quality work, apply two coats of Fassiprim, sanding between each coat carefully. In some cases, the 2 coats of Fassiprim can be replaced by 1 thick coat of Fassicoat. For exterior works, it is advisable to apply an impregnating coat of Fassiforce on bare or stripped wood, or on low grade wood. Do not use Fassicoat on metallic substrate; in this situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Apply in a dry and well-ventilated area. Temperature minimum 10°C. Relative humidity maximum 80%.

PÅFØRING OG FORTYNDING: PENSEL

Do not dilute

PÅFØRING OG FORTYNDING: RULLE

Do not dilute

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Nozzle: 09 - 013 / Pressure: 180 bars. Do not dilute.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Do not dilute

RENGØRING AF UDSTYR/SPILD

White spirit or Thinner 22.

BEMÆRKNINGER

Apply Fassilux in thin layers.

SIKKERHEDSDATA

VOC-niveau:	300
VOC-kategori:	A/d
VOC-grænse:	300 g/l (2010)
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not indirect sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 29/11/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu