



FASSILUX® SATIN

First quality satin gloss

- Simple and fast application
- Excellent flow
- Excellent scratch and wear resistance
- Good outdoor durability, weatherproof
- Quick drying

FASSILUX® SATIN

DESCRIPTION

First quality satin gloss alkyd enamel, for interior and exterior application

RECOMMENDED USE

Topcoat for interior and exterior woodwork.

TECHNICAL DATA

| | |
|---------------------------|-------------------|
| Density (g/cm³): | 1,34 - 1,37 |
| Gloss Level: | Satin |
| Gloss level at 60°: | +/- 30% |
| Solids Content in weight: | 70 - 73% (wit) |
| Solids content in volume: | 53 - 56 % (weiss) |

DRY TIMES BY 20° C/RH 50%

| | |
|----------------|-------------|
| Touch dry: | 4 - 5 hours |
| Dry to handle: | 5 - 6 hours |
| Dry to recoat: | 24 hours |
| Fully cured: | ± 1 week |

RECOMMENDED WET FILM THICKNESS

55 µm

RECOMMENDED DRY FILM THICKNESS

30 µm

THEORETICAL CONSUMPTION

18 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Priming coat: Fassiprim. For top quality painting work, apply two coats of Fassiprim, sanding between each coat carefully. For exterior works, it is advisable to apply an impregnating coat of FassiForce on bare or stripped wood, or on low grade wood. Do not use Fassicoat on metallic substrates; in this situation, use a tintable Rust-Oleum anticorrosion primer. Block wood knots and sap streaks with Zinsser primer B-I-N. Block tannin or other typical bleeding substances from redwoods etc, and/or block graffiti's, with Zinsser primer Cover-Stain.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

- Apply in a dry and well-ventilated area.
- Minimum temperature: 10°C. Maximum relative humidity: 80%

APPLICATION & THINNING: BRUSH

Do not dilute

APPLICATION & THINNING: ROLLER

Do not dilute

APPLICATION & THINNING: AIRLESS SPRAY

- Nozzle: 013 - 015 / Pressure: 180 bars.
- Do not dilute.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Do not dilute

CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22

REMARKS

Do not use Fassilux Satin on Noxyde for outside works. In these cases, use either Fassilux or Pegacryl Satin.

SAFETY DATA

| | |
|---------------------------|--|
| VOC category: | A/d |
| VOC limit: | 400 g/l (2007) / 300 g/l (2010) |
| Remarks regarding safety: | Consult Safety Data Sheet and Safety Information printed on the can. |

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

Date issued: 07/02/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu