



Quality Paints since 1845
MATHYS®



FASSIPRIM AQUA XPE

Waterbased primer

- Water based, matt acrylic
- Easy to apply
- Quick drying, quick to sand
- Good coverage
- Excellent adhesion and flow



FASSIPRIM AQUA XPE

DESCRIPTION

Waterbased, moisture regulating primer for long- lasting indoor and outdoor timberwork.

RECOMMENDED USE

Primer for different types of wood and well cleaned, well adhering old coatings.

TECHNICAL DATA

Density (g/cm ³):	± 1,3
Gloss Level:	Matt
Solids Content in weight:	± 53 %
Solids content in volume:	± 39 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to recoat:	3 hours
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS

100 µm

RECOMMENDED DRY FILM THICKNESS

35 µm

THEORETICAL CONSUMPTION

± 10 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

- New work: substrate has to be clean, dry and free of fats. Deteriorated wood has to be removed to the sound wood. For very porous substrates like fir and pine it is recommended to apply a second primer coat.
- Existing work: clean, degrease and sand. Remove loose, flaking or cracked paint layers. Treat bare spots as new work.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

10-30 degrees C. Relative humidity < 80%. Temperature of the substrate at least 3 degrees C above the dewpoint.

APPLICATION & THINNING: BRUSH

Dilute, if necessary, up to maximum 5% volume with water.

APPLICATION & THINNING: ROLLER

Dilute, if necessary, up to maximum 5% volume with water.

APPLICATION & THINNING: AIRLESS SPRAY

- Nozzle: 0.013 inch / Pressure: 120 - 150 bars.
- Thinning 3% volume water.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

- Nozzle 1,5 - 2,0 mm / Pressure: 2 - 3 bars.

- Thinning 10 - 15% volume water.

CLEANING OF EQUIPMENT / SPILLS

Warm water.

SAFETY DATA

VOC level:	17 g/l max.
VOC category:	A/g
VOC limit:	30 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 08/09/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu