

Quality Paints since 1845
MATHYS[®]



FASSIPRIM

Primer

- Solvent based primer-surfacer containing soya-alkyd resins
- Excellent flow out and adhesion on wood
- Moisture controlling
- High covering capacity
- Quick drying



FASSIPRIM

POPIS PRODUKTU (DLOUHÝ)

Solvent borne primer-surfacer. Moisture regulating paint for indoor and outdoor timber work.

DOPORUČENÉ POUŽITÍ

Primer on wood and undercoat for satin gloss and high gloss alkyd enamels.

TECHNICAL_DATA

Hustota (g/cm ³):	1,33 – 1,38
Úroveň lesku:	Satin
Obsah pevných látek v hmotnosti:	70 – 73 %
Obsah pevných látek v objemu:	52 – 56 %

DRY_TIMES_BY_20

Dotykem suché:	3 hours
Suché na manipulaci:	4-5 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	± 1 week

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

65 ùm

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

35 ùm

TEORETICKÁ SPOTŘEBA

15 m²/l per coat

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

The substrate must be stable, clean and dry. Bare wood: degrease, sand and remove dust. For exterior works on wood that is not of first quality or that is damaged, it is advisable to apply a coat of FassiForce first. Do not apply on metallic substrates, in this case Combiprimer has to be used. Old unsound paints: remove paint, degrease, dry sanding, then proceed in the same way as for bare wood or metallic substrates. Chalking paints: remove all non-adhering parts, dedust and hereafter, apply a coat of Fixonal. Old sound paints: sand and clean with white spirit.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

- Apply in a dry and well-ventilated area.
- Minimum temperature: 10°C. Maximum relative humidity: 80%.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Do not dilute.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

Do not dilute.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

- Nozzle: 015 / Pressure: 180 bar.
- Do not dilute.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Do not dilute.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit or Thinner 22.

DATA SAFETY DATA

Úroveň těkavých organických látek:	350 g/l max.
Kategorie VOC:	A/g
Limitní hodnota VOC:	350 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chiène
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu