



FASSIPRIM

Primer

- Solvent based primer-surfacer containing soya-alkyd resins
- · Excellent flow out and adhesion on wood
- Moisture controlling
- High covering capacity
- Quick drying

FASSIPRIM

DESCRIPTION

Solvent borne primer-surfacer. Moisture regulating paint for indoor and outdoor timber work.

RECOMMENDED USE

Primer on wood and undercoat for satin gloss and high gloss alkyd enamels.

TECHNICAL DATA

DRY TIMES BY 20° C/RH 50%

 $\begin{array}{lll} \mbox{Touch dry:} & 3 \mbox{ hours} \\ \mbox{Dry to handle:} & 4-5 \mbox{ hours} \\ \mbox{Dry to recoat:} & 24 \mbox{ hours} \\ \mbox{Fully cured:} & \pm 1 \mbox{ week} \\ \end{array}$

RECOMMENDED WET FILM THICKNESS

65 ùm

RECOMMENDED DRY FILM THICKNESS

35 ùm

THEORETICAL CONSUMPTION

15 m²/l per coat

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrate must be stable, clean and dry. Bare wood: degrease, sand and remove dust. For exterior works on wood that is not of first quality or that is damaged, it is advisable to apply a coat of FassiForce first. Do not apply on metallic substrates, in this case Combiprimer has to be used. Old unsound paints: remove paint, degrease, dry sanding, then proceed in the same way as for bare wood or metallic substrates. Chalking paints: remove all non-adhering parts, dedust and hereafter, apply a coat of Fixonal. Old sound paints: sand and clean with white spirit.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

- Apply in a dry and well-ventilated area.
- Minimum temperature: 10°C. Maximum relative humidity: 80%.

APPLICATION & THINNING: BRUSH

Do not dilute.

APPLICATION & THINNING: ROLLER

Do not dilute.

APPLICATION & THINNING: AIRLESS SPRAY

- Nozzle: 015 / Pressure: 180 bar.
- Do not dilute.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Do not dilute.

CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22.

SAFETY DATA

 VOC level:
 350 g/l max.

 VOC category:
 A/g

 VOC limit:
 350 g/l (2010)

Remarks regarding safety: Consult Safety Data Sheet and Safety Information

printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 13/03/2023

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V. Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T: +31 (0) 165 593 636 F: +31 (0) 165 593 600 info@rust-oleum.eu Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 info@rust-oleum.eu N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu