

Quality Paints since 1845
MATHYS[®]



FASSITEK[®]

Wood stain

- Transparent and light-stable
- Penetrates for deep protection
- Non film-forming
- Enhances the wood structure
- Microporous, allows the wood to breathe



POPIS PRODUKTU (DLOUHÝ)

Fassitek is a solvent based stain with a base of special alkyd resins. These stains are very effective in impregnating wood and protecting many types of wood from weathering and UV rays

DOPORUČENÉ POUŽITÍ

Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance - micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

TECHNICAL DATA

Hustota (g/cm ³):	0,87 - 0,90
Úroveň lesku:	Semi-Matt
Obsah pevných látek v hmotnosti:	± 38 %
Obsah pevných látek v objemu:	± 30 %

DRY TIMES BY 20

Dotykem suché:	3 hours (15 m ² /l)
Suché na manipulaci:	3 hours (15 m ² /l)
Suchý nátěr:	24 hours

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 micron (cons.: 10 m²/l)

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

30 micron (cons.: 10 m²/l)

TEORETICKÁ SPOTŘEBA

10 - 15 m²/l

PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit, Afzelia with ammonia water. Old stripped paint: rub down up to the bare not impregnated wood fibre and make dust free. Maintenance on Fassitek: clean substrate with white spirit and apply 2 or 3 thin coats.

NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC

By preference, apply undiluted.

APLIKACE A ŘEDĚNÍ: VÁLEČEK

By preference, apply undiluted.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

By preference, apply undiluted.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit or Thinner 22

POZNÁMKY

Incorrect use of Fassitek means that it can still be fully or partly removed with Thinner 22 within the first few days after application

DATA SAFETY DATA

Úroveň těkavých organických látek:	565 g/l max
Kategorie VOC:	A/f
Limitní hodnota VOC:	700 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can.

DOBA POUŽITELNOSTI

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

last updated: 07/02/2025

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu