



**FASSITEK®**

## Wood stain

- Transparent and light-stable
- Penetrates for deep protection
- Non film-forming
- Enhances the wood structure
- Microporous, allows the wood to breathe



## DESCRIPTION

Fassitek is a solvent based stain with a base of special alkyd resins. These stains are very effective in impregnating wood and protecting many types of wood from weathering and UV rays

## RECOMMENDED USE

Transparent and colour fast - accentuates wood grains - very penetrating product - penetrative treatment and protection - excellent UV-rays and weather resistance - micro porous, so no risk of blisters or peeling off - easier maintenance - not a film former.

## TECHNICAL DATA

Density (g/cm³):	0,87 - 0,90
Gloss Level:	Semi-Matt
Solids Content in weight:	± 38 %
Solids content in volume:	± 30 %

## DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours (15 m²/l)
Dry to handle:	3 hours (15 m²/l)
Dry to recoat:	24 hours

## RECOMMENDED WET FILM THICKNESS

100 micron (cons.: 10 m²/l)

## RECOMMENDED DRY FILM THICKNESS

30 micron (cons.: 10 m²/l)

## THEORETICAL CONSUMPTION

10 - 15 m²/l

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit, Afzelia with ammonia water. Old stripped paint: rub down up to the bare not impregnated wood fibre and make dust free. Maintenance on Fassitek: clean substrate with white spirit and apply 2 or 3 thin coats.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

## APPLICATION & THINNING: BRUSH

By preference, apply undiluted.

## APPLICATION & THINNING: ROLLER

By preference, apply undiluted.

## APPLICATION & THINNING: AIRLESS SPRAY

By preference, apply undiluted. Nozzle: 09 - 013 / Pressure: 150 bars.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

By preference, apply undiluted.

## CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22

## REMARKS

Incorrect use of Fassitek means that it can still be fully or partly removed with Thinner 22 within the first few days after application

## SAFETY DATA

VOC level:	565 g/l max
VOC category:	A/f
VOC limit:	700 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 07/02/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)