



FASSITEK[®] THIXO

Slight thixotropic solvent based wood stain

- Transparent and light-stable
- Thixotropic alkyd resins
- Penetrates for deep protection
- Non film-forming
- Enhances the wood structure

FASSITEK® THIXO

DESCRIPTION

Fassitek® Thixo is an easy to apply thixotropic stain. This Fassitek® version has all the protective and cosmetic qualities of the classic Fassitek®, but is slightly thicker in texture. This means that a thicker coating of the product can be applied and makes it more convenient to use, especially for overhead work.

RECOMMENDED USE

Protective and decorative impregnation of interior and exterior woodwork.
Remark: colourless Fassitek is only suitable for internal use

TECHNICAL DATA

Density (g/cm³):	0,86-0,89
Gloss Level:	Semi-Matt
Solids Content in weight:	37-40 %
Solids content in volume:	30-33 %

DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours
Dry to handle:	3 hours
Dry to recoat:	24 hours

RECOMMENDED WET FILM THICKNESS

100 microns

RECOMMENDED DRY FILM THICKNESS

32 microns

THEORETICAL CONSUMPTION

10 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application

SURFACE PREPARATION

New wood: rub down and make it dust free. Tropical wood is degreased with white spirit;
Afzelia with ammonia water.
Old stripped paint: rub down to the bare not impregnated wood fibre and make dust free.
Maintenance on Fassitek Thixo: clean substrate with white spirit and apply 2 or 3 thin coats.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

By preference, apply undiluted.

APPLICATION & THINNING: ROLLER

By preference, apply undiluted.

APPLICATION & THINNING: AIRLESS SPRAY

By preference, apply undiluted. Nozzle: 0.009 - 0.013 / Pressure: 150 bar

APPLICATION & THINNING: AIR-ATOMISED SPRAY

By preference, apply undiluted.

CLEANING OF EQUIPMENT / SPILLS

White Spirit or Thinner 22

REMARKS

Incorrect use of Fassitek Thixo means that it can still be fully or partially removed with Thinner 22 within the first few days after application.

SAFETY DATA

VOC level:	550 g/l
VOC readymix:	550 g/l
VOC category:	A/f
VOC limit:	700 g/l
Remarks regarding safety:	Consult Material Safety Data Sheet and safety information printed on the can

SHELF LIFE

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight, at temperatures between 5 and 35°C.

Date issued: 05/10/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu