



## FASSITHANE GLOSS

### Wood Varnish

- Quick drying
- Does not yellow
- Scratch and wear resistant
- No tendency to wrinkle when applying thick layers
- Satin and Gloss versions: use indoors and outdoors

# FASSITHANE GLOSS

## DESCRIPTION

First quality polyurethane wood varnish for interior and exterior use

## RECOMMENDED USE

Hard, durable finishing varnish on wood for interior and exterior use.

## TECHNICAL DATA

Density (g/cm³):	0,90 - 0,92
Gloss Level:	Gloss
Gloss level at 60°:	>90%
Solids Content in weight:	49,5 – 51,5 %
Solids content in volume:	42 - 44 %

## DRY TIMES BY 20° C/RH 50%

Touch dry:	1½ hours
Dry to handle:	2 hours
Dry to recoat:	6 hours
Fully cured:	7 days

## RECOMMENDED WET FILM THICKNESS

65 µm

## RECOMMENDED DRY FILM THICKNESS

30 µm

## THEORETICAL CONSUMPTION

± 15 m²/l per coat

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

The substrate must be smooth and completely dry and clean. New wood: rub down and make dustfree (use a cloth damped in white spirit). Degrease resinous or exotic wood with thinner. Remove old varnish layers with a paint stripper (Rapid Super). After this rub down lightly and clean with white spirit. Old varnish layers with good adhesion: rub down lightly and clean. Restore discoloured parts with Fassitek and rub down.

### New wood:

- Impregnate with FassiForce or Fassitek if it is necessary to colour the wood.
- If colouring is not necessary, first apply a thinned coat Fassithane Gloss.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Apply in a dry and well-ventilated area. Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 80%. The substrate temperature must be at least 3°C above dew point.

## APPLICATION & THINNING: BRUSH

Do not dilute.

## APPLICATION & THINNING: ROLLER

Do not dilute.

## APPLICATION & THINNING: AIRLESS SPRAY

Do not dilute.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Do not dilute.

## CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner 22.

## REMARKS

In case of exterior applications use at least 3 coats Fassithane Gloss. In case the recoat time between successive coats is longer than 24 hours, it is necessary to clean the surface with a cloth soaked in white spirit in order to achieve a good adhesion.

## SAFETY DATA

VOC level:	400 g/l max.
VOC category:	A/e
VOC limit:	400 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 23/06/2025

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)