



FASSITHANE MATT

Matt Wood Varnish

- Quick drying
- Does not yellow
- Scratch and wear resistant
- No tendency to wrinkle when applying thick layers
- Use indoors

FASSITHANE MATT

BESKRIVELSE

First quality polyurethane wood varnish for interior use.

ANBEFALET BRUG

Hard, durable finishing varnish on wood for interior use.

TEKNISK DATA

Tæthed:	0,93 - 0,95
Glansgrad:	Mat
Faststofindhold i vægt:	53 - 55 %
Tørstofindhold i volumen:	44 - 46 %

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1½ hour
Håndteringstør:	2 hours
Genbehandlingstør:	6 hours
Fuldt hærdet:	7 days

ANBEFALET VÅDFILM TYKKELSE

65 µm

ANBEFALET TØRFILM TYKKELSE

35 µm

TEORETISK FORBRUG

± 15 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The substrate must be smooth and completely dry and clean. New wood: rub down and make dustfree (use a cloth dampened in white spirit). Degrease resinous or exotic wood with thinner. Remove old varnish layers with a paint stripper (Rapid Super). After this rub down lightly and clean with white spirit. Old varnish layers with good adhesion: rub down lightly and clean. Restore discoloured parts with Fassitek and rub down.

New wood:

- Impregnate with FassiForce or Fassitek if it is necessary to colour the wood.
- If colouring is not necessary, first apply a thinned coat Fassithane Matt.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Apply in a dry and well-ventilated area. Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 80%. The substrate temperature must be at least 3°C above dew point.

PÅFØRING OG FORTYNDING: PENSEL

Do not dilute.

PÅFØRING OG FORTYNDING: RULLE

If necessary dilute with maximum 10% volume white spirit or Thinner 22.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Do not dilute.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Do not dilute.

RENGØRING AF UDSKYR/SPILD

White spirit or Thinner 22

BEMÆRKNINGER

In case the recoat time between successive coats is longer than 24 hours, it is necessary to clean the surface with a cloth soaked in white spirit in order to achieve a good adhesion.

SIKKERHEDSDATA

VOC-niveau:	400 g/l m
VOC-kategori:	A/e
VOC-grænse:	400 g/l (2010)
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Udstedelsesdato: 07/06/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu