



Quality Paints since 1845
MATHYS®



FASSITHANE SATIN

Wood Varnish

- Quick drying
- Does not yellow
- Scratch and wear resistant
- No tendency to wrinkle when applying thick layers
- Use indoors and outdoors

FASSITHANE SATIN

BESKRIVNING

First quality polyurethane wood varnish for interior and exterior use

REKOMMENDERAD ANVÄNDNING

Hard, durable finishing varnish on wood for interior and exterior use.

TEKNISK DATA

Densitet:	0,93 - 0,95
Glansnivå:	Satin
Torrsubstansvikt:	51 - 53 %
Torrsubstansvolym:	43 - 45 %

TORKTIDER VID 20°C/RELATIV LUFTFUKTIGHET 50%

Beröringstorr:	1½ hour
Hanteringstorr:	2 hours
Övermålningsbar:	6 hours
Fullt härdad:	7 days

REKOMMENDERAD VÅTFILMSTJOCKLEK

65 µm

REKOMMENDERAD TORRFILMSTJOCKLEK

30 µm

TEORETISK FÖRBRUKNING

± 15 m²/l per coat

PRAKTISK FÖRBRUKNING

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

YTFÖRBEREDELSE

The substrate must be smooth and completely dry and clean. New wood: rub down and make dustfree (use a cloth damped in white spirit). Degrease resinous or exotic wood with thinner. Remove old varnish layers with a paint stripper (Rapid Super). After this rub down lightly and clean with white spirit. Old varnish layers with good adhesion: rub down lightly and clean. Restore discoloured parts with Fassitek and rub down.

New wood:

- Impregnate with FassiForce or Fassitek if it is necessary to colour the wood.
- If colouring is not necessary, first apply a thinned coat Fassithane Satin.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICERINGSFÖRHÅLLANDEN

Apply in a dry and well-ventilated area. Temperature of air, substrate and coating material between 10 and 35°C and relative humidity below 80%. The substrate temperature must be at least 3°C above dew point.

APPLICERING OCH SPÄDNING: PENSEL

Do not dilute.

APPLICERING OCH SPÄDNING: ROLLER

If necessary dilute with max. 10% white spirit or Thinner 22.

APPLICERING OCH SPÄDNING: AIRLESSPRUTA

Do not dilute.

APPLICERING OCH SPÄDNING: TRYCKLUFTSSPRUTA

Do not dilute.

RENGÖRING AV UTRUSTNING/SPILL

White spirit or Thinner 22

ANMÄRKNINGAR

In case of exterior applications use at least 3 coats Fassithane Satin. In case the recoat time between successive coats is longer than 24 hours, it is necessary to clean the surface with a cloth soaked in white spirit in order to achieve a good adhesion.

SÄKERHETSDATA

VOC-nivå:	400 g/l max.
VOC-kategori:	A/e
VOC-gräns:	400 g/l (2010)
Anmärkningar om säkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HÅLLBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utgivet den: 07/02/2025

Tillgängliga färger och förpackningsstorlekar: Se respektive produktsida på www.rust-oleum.eu för en översikt över tillgängliga färger och förpackningsstorlekar.

Förbehåll: Informationen i detta produktdatablad är korrekt så långt vi känner till och ges i god tro men utan garanti. Vi förutsätter att användaren självständigt har tagit ställning till lämpligheten av våra produkter för hans eller hennes egna syften. Under inga omständigheter är Rust-Oleum Europe ansvarigt för indirekta skador eller följdsador. Produkterna ska förvaras, hanteras och användas under förhållanden som överensstämmer med Rust-Oleum Europes rekommendationer i den senaste utgåvan av produktdatabladet. Det är användarens ansvar att säkerställa att han/hon har den aktuella utgåvan. Senaste utgåvan av produktdatabladet kan erhållas kostnadsfritt från www.rust-oleum.eu eller vår kundtjänst. Rust-Oleum Europe förbehåller sig rätten att ändra egenskaperna i sina produkter utan föregående avisering.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu