

Quality Paints since 1845
MATHYS[®]



FIXONAL

Colourless fixating agent

- Fixing and reinforcing
- Alkali resistant
- Quick drying
- Flexible

WWW.MATHYSPAINTS.EU

FIXONAL

ОПИСАНИЕ

Fixating varnish based on acrylic polymers to strengthen all porous or chalking substrates.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Fixation of chalking substrates. Reinforces the adhesion of the new coat on the old paint and makes more flexible.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	0,81 - 0,83
Гланцово ниво при 60°:	> 90%
Съдържание на сухо вещество (по тегло):	19%
Съдържание на сухо вещество (по обем):	15%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	± 45 minutes
Сух за употреба:	± 1 hour
Готов за повторно нанасяне:	± 2 - 4 hours
group_dry_40_full_cure:	± 1 day

МОКЪР СЛОЙ

100 µm

СУХ СЛОЙ

15 µm

РАЗХОДНА НОРМА

± 10 - 15 m²/l, according to the porosity of the substrate.

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

НАЧИН НА УПОТРЕБА

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

By preference, do not dilute.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

By preference, do not dilute

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Not recommended

ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Not recommended

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

White spirit

ЗАБЕЛЕЖКИ

Fixonal does not improve the adhesion of old paint coats on the substrate.

ДАНИИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	700 g/l max.
Категория ЛОС:	A/h
group_voc_40_limit:	750 g/l (2007) / 750 g/l (2010)
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

Дата на издаване: 09/12/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu