

Quality Paints since 1845
MATHYS[®]



FIXONAL

Colourless fixating agent

- Fixing and reinforcing
- Alkali resistant
- Quick drying
- Flexible

WWW.MATHYSPAINTS.EU

FIXONAL

BESKRIVELSE

Fixating varnish based on acrylic polymers to strengthen all porous or chalking substrates.

ANBEFALET BRUG

Fixation of chalking substrates. Reinforces the adhesion of the new coat on the old paint and makes more flexible.

TEKNISK DATA

Tæthed:	0,81 - 0,83
Glansgrad ved 60°:	> 90%
Faststofindhold i vægt:	19%
Tørstofindhold i volumen:	15%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	± 45 minutes
Håndteringstør:	± 1 hour
Genbehandlingstør:	± 2 - 4 hours
Fuldt hærdet:	± 1 day

ANBEFALET VÅDFILMYKKELSE

100 µm

ANBEFALET TØRFILMYKKELSE

15 µm

TEORETISK FORBRUG

± 10 - 15 m²/l, according to the porosity of the substrate.

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surfaces to be treated must be dry, clean and adhering. Chalking substrates must be rubbed down with a hard brush and dusted off. Rub down glossy coats. Degrease if necessary. After drying, apply the topcoat as quickly as possible.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Work in a dry and well-ventilated area. > 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

By preference, do not dilute.

PÅFØRING OG FORTYNDING: RULLE

By preference, do not dilute

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Not recommended

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Not recommended

RENGØRING AF UDSKYR/SPILD

White spirit

BEMÆRKNINGER

Fixonal does not improve the adhesion of old paint coats on the substrate.

SIKKERHEDSDATA

VOC-niveau:	700 g/l max.
VOC-kategori:	A/h
VOC-grænse:	750 g/l (2007) / 750 g/l (2010)
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C

Udstedelsesdato: 20/12/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu