





MATHY-CRYL MAT

Waterbased matt paint for indoor use

- Easy and completely spatter-free roller application
- Even flat finish without overlaps
- Covers perfectly in 2 coats on most kinds of porous and not porous substrates without gloss differences
- · Nearly odourless

MATHY-CRYL MAT

RECOMMENDED USE

Inner decoration on most common substrates such as plaster, bricks and concrete. Mathycryl Mat can also be applied on old paint coats in good condition and most wallpaper paintable texture and glass fibre.

TECHNICAL DATA

Density (g/cm³): 1.38 - 1.41
Gloss Level: Matt
Gloss level at 60°: 2%
Solids Content in weight: 48 - 51%
Solids content in volume: 28 - 32%

DRY TIMES BY 20° C/RV 50%

Touch dry: 30 minutes
Dry to handle: Not applicable
Dry to recoat: 3 hours
Fully cured: ± 1 week

RECOMMENDED WET FILM THICKNESS

 \pm 140 μm

RECOMMENDED DRY FILM THICKNESS

 $\pm 45 \mu m$

THEORETICAL CONSUMPTION

6 - 8 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Always work on a dry and stable substrate. On porous substrates, no specific pre-treatment is required in most cases. Slightly chalking substrates or new plaster should first be impregnated with Pegaprim Xpress. Damp substrates or nicotine stains should be isolated with Pegaprim Isofix.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Apply at a temperature of min. 5°C and a R.H. of max. 80%.

APPLICATION & THINNING: BRUSH

Apply undiluted.

APPLICATION & THINNING: ROLLER

Textured polyamide 20 mm. Apply undiluted.

APPLICATION & THINNING: AIRLESS SPRAY

If necessary, dilute with 2 - 5% of water. Nozzle: 016 - 018 / Pressure: 200 bars.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended.

CLEANING OF EQUIPMENT / SPILLS

Water.

SAFETY DATA

 VOC level:
 20 g/l

 VOC category:
 A/a

 VOC limit:
 30 g/l (2010)

SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 31/08/2022

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V Zilverenberg 16 5234 GM 's-Hertogenbosch The Netherlands T: +31 (0) 165 593 636 F: +31 (0) 165 593 600 Tor Coatings Ltd (Rust-Oleum Industrial Shadon Way, Portobello Ind. Estate Birtley, Chester le-Street DH3 2RE United Kingdom T: +44 (0)1914 113 146 F: +44 (0)1914 113 147 info@rust-oleum.eu

Rust-Oleum France S.A.S 38, av. du Gros Chêne 95322 Herblay France T: +33(0) 130 40 00 44 F: +33(0) 130 40 99 80 N.V. Martin Mathys S.A. Kolenbergstraat 23 3545 Zelem Belgium T: +32 (0) 13 460 200 F: +32 (0) 13 460 201 info@rust-oleum.eu