Quality Paints since 1845

MATHYS®

MURFILL® RENOVATION PAINT

Elastic decorative renovation paint

- > 500 % elastic
- Lasting elasticity till -30°C
- Water vapour permeable
- Matt aspect
- Excellent resistance against aging and contamination

MURFILL® RENOVATION PAINT

DESCRIPTION
Matt and long-lasting elastic renovation paint. Ideal for renovation and decoration of historical and new buildings.

DOPORUČENÉ POUŽITÍ
Renovation and decoration of exterior walls and façades.

TECHNICAL_DATA

Hustota (g/cm³):	1,33 - 1,37 (weiss)
Úroveň lesku:	Matt
Obsah pevných látek v hmotnosti:	60 - 63 %
Obsah pevných látek v objemu:	47 - 50 %
Propustnost pro vodní páru:	17g/m²/24h and Sd (m) = 1,4

DRY TIMES BY 20º C/RH 50%

Dotykem suché:	45 minutes
Suché na manipulaci:	± 8 hours
Suchý nátěr:	24 hours
Plně vytvrzené:	2 days

DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU
150 µm (cons. : 200 g/m²)

DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU
70 µm (cons.: 200 g/m²)

TEORETICKÁ SPOTŘEBA
- Normal consumption: min. 400 g/m² (2 coats).
- Application by brush or roller: 200 – 300 g/m² per coat, in function of the application method and the substrate.
- Application by airless: 200 – 500 g/m² per coat, in function of the application method and the substrate.

PRAKTICKÁ SPOTŘEBA
Coverage is theoretical and depends on many factors such as porosity and roughness of the substrate and material losses during application.

PŘÍPRAVA POVRCHU
Substrate must be clean, sound and dry (max. 6% substrate humidity) prior to application. Remove any moss, algae, etc. with a suitable detergent
Previously painted surfaces (in good condition): apply directly after thorough brushing. Chalky paints or bare substrates should first be primed with Fixonal oor Pegafix. On smooth and non-porous substrates, prime with white Pegalink or with one coat of Noxyde (except white, diluted with 20% of water.
For stain, graffiti blocking and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.
Cracks < 0,5 mm will be filled with Murfill Renovation Paint. Cracks > 0,5 mm will be filled with Elastofill or Mur-Filler acrylic sealants.

NÁVOD K POUŽITÍ
To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PODMÍNKY POUŽITÍ
Minimum temperature: 5°C. Max. 80 % R.H.

APLIKACE A ŘEDĚNÍ: ŠTĚTEC
Use a synthetic brush for application of waterbased products.

APLIKACE A ŘEDĚNÍ: VÁLEČEK
Use long nap roller (texture polyamide roller 20 mm) or specific façade roller 24 mm. Depending on the roughness of the substrate.

APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ
If necessary, dilute with 2 - 5% volume water. Nozzle: 13 – 15 / Pressure: 200 bars.

APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ
Not possible.

ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ
Water.

POZNÁMKY
For any information regarding options of guarantee with this system, please contact Technical Service.

SAFETY DATA

Úroveň těkavých organických látek:	30 g/l max
Kategorie VOC:	A/i
Limitní hodnota VOC:	140 g/l (2007) / 140 g/l (2010)
Poznámky k bezpečnosti:	Consult Safety Data Sheet and Safety Information printed on the can

DOBA POUŽITELNOSTI
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last_updated: 22/06/2026

footer_data_colors_pack_sizes: footer_data_colors_pack_sizes.value

footer_data_disclaimer: footer_data_disclaimer.value

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu