



MURFILL® RP SILOXAN NF

Hydrophobic, renovate and color in one

- Excellent resistance to aging and pollution
- Self-cleaning, hydrophobic
- Pearly effect
- Water vapor permeable
- Very good coverage

MURFILL® RP SILOXAN NF

ОПИСАНИЕ

Very matt elastic renovation coating for exterior walls based on acrylates-siloxanes.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Waterproofing of old walls and facades. Resistant against hairline cracks up to 0,2 mm. Protection and renovation of old and new outside walls, micro-fissure grid.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

Bare substrates or well conserved undercoats, use Pegaprim Exterior as primer. On powdering substrates which need to be reinforced: prime with MurPrim S NF.

- Smoot, dense substrates: Noxyde diluted with 25% water (cons. 200 g/m²)
- Decorative: 1 coat Murfill RP Siloxan NF (cons. 500 g/m²)
- Waterproofing: 1 coat Murfill RP Siloxan NF cons. 500 g/m²)

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³): 1,40 (depending on colour)
Гланцово ниво: Мат
gloss_level_85: < 2,0% - at angle of 85 °; very mat.
Съдържание на сухо вещество (по тегло): 68% (depending on colour)

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 4 hours
Сух за употреба: 4 -8 hours
Готов за повторно нанасяне: 24 - 48 hours

РАЗХОДНА НОРМА

500 g/m²

КОНСУМАЦИЯ

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be completely clean, dry and sound. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution.

НАЧИН НА УПОТРЕБА

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

УСЛОВИЯ ЗА НАНАСЯНЕ

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80%. No condensation during drying time. Low temperatures and/or high relative humidity extend the drying time.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Synthetic brushes for water dispersed paints. Do not dilute

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Textured polyamide rollers 20 mm or long haired brushes according to roughness of substrate. Do not dilute.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water

ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС: 40 g/l max.
Категория ЛОС: A/c
group_voc_40_limit: 40 g/l (2010)
Забележки относно безопасността: Consult safety data sheet and Safety information printed on the can.

СРОК НА ГОДНОСТ

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Дата на издаване: 02/10/2025

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu