



## **MURFILL® RP SILOXAN NF**

# **Hydrophobic, renovate and color in one**

- Excellent resistance to aging and pollution
- Self-cleaning, hydrophobic
- Pearly effect
- Water vapor permeable
- Very good coverage

# MURFILL® RP SILOXAN NF

## BESKRIVELSE

Very matt elastic renovation coating for exterior walls based on acrylates-siloxanes.

## ANBEFALET BRUG

Waterproofing of old walls and facades. Resistant against hairline cracks up to 0,2 mm.  
Protection and renovation of old and new outside walls, micro-fissure grid.

## ANBEFALET SYSTEM

Bare substrates or well conserved undercoats, use Pegaprim Exterior as primer.  
On powdering substrates which need to be reinforced: prime with MurPrim S NF.

- Smoot, dense substrates: Noxyde diluted with 25% water (cons. 200 g/m<sup>2</sup>)
- Decorative: 1 coat Murfill RP Siloxan NF (cons. 500 g/m<sup>2</sup>)
- Waterproofing: 1 coat Murfill RP Siloxan NF cons. 500 g/m<sup>2</sup>)

## TEKNISK DATA

|                         |                                      |
|-------------------------|--------------------------------------|
| Tæthed:                 | 1,40 (depending on colour)           |
| Glansgrad:              | Mat                                  |
| Glansgrad ved 85°:      | < 2,0% - at angle of 85 °; very mat. |
| Faststofindhold i vægt: | 68% (depending on colour)            |

## TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

|                    |               |
|--------------------|---------------|
| Berøringstør:      | 4 hours       |
| Håndteringstør:    | 4 -8 hours    |
| Genbehandlingstør: | 24 - 48 hours |

## TEORETISK FORBRUG

500 g/m<sup>2</sup>

## PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FORBEHANDLING AF OVERFLADEN

The substrate must be completely clean, dry and sound. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution.

## BRUGSANVISNING

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

## ANVENDELSESBETINGELSER

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80%. No condensation during drying time. Low temperatures and/or high relative humidity extend the drying time.

## PÅFØRING OG FORTYNDING: PENSEL

Synthetic brushes for water dispersed paints. Do not dilute

## PÅFØRING OG FORTYNDING: RULLE

Textured polyamide rollers 20 mm or long haired brushes according to roughness of substrate. Do not dilute.

## RENGØRING AF UDSYR/SPILD

Water

## SIKKERHEDSDATA

|                            |                                                                      |
|----------------------------|----------------------------------------------------------------------|
| VOC-niveau:                | 40 g/l max.                                                          |
| VOC-kategori:              | A/c                                                                  |
| VOC-grænse:                | 40 g/l (2010)                                                        |
| Bemærkninger om sikkerhed: | Consult safety data sheet and Safety information printed on the can. |

## HOLDBARHED

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 28/11/2024

**Tilgængelige farver og pakningsstørrelser:** Der henvises til den respektive produktside på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

**Ansvarsfraskrivelse:** Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu) eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)