



Quality Paints since 1845
MATHYS®



MURFILL® WP PLUS NF

Elastic waterproofing system

- UV-crosslinking system, acrylic
- Very durable system, guarantee
- Very flexible paint film, crack-bridging
- Permanently elastic
- Waterproof



MURFILL® WP PLUS NF

BESKRIVELSE

Smooth, semi-thick elastic cladding for facades. Based on acrylic resins with UV-cross-linking system, for waterproofing facades. Water based.

ANBEFALET BRUG

Waterproofing of facades, crack bridging from 0.2 mm to 2 mm

TEKNISK DATA

| | |
|---------------------------|--------------------------------|
| Tæthed: | 1,5 (± af hankelijk van kleur) |
| Glansgrad: | Mat |
| Glansgrad ved 85°: | 2% |
| Faststofindhold i vægt: | 74 % (±afhankelijk van kleur) |
| Tørstofindhold i volumen: | 62 % (±afhankelijk van kleur) |

TEORETISK FORBRUG

500 g/m²/coat

PRAKTISK FORBRUG

The consumption is theoretical and depends on many factors such as roughness and porosity of the substrate and the application conditions.

FORBEHANDLING AF OVERFLADEN

The surface must be completely clean, dry and healthy. In the event of contamination by microorganisms, pre-clean with an anti-moss solution.

BRUGSANVISNING

Before use, the coatings must be stirred intensively to a good homogeneity

ANVENDELSESBETINGELSER

Minimum temperature 5 °C, maximum temperature 35 °C and maximum relative humidity 80%. No condensation during the drying time. A low temperature and/or a high relative humidity extend the drying time.

PÅFØRING OG FORTYNDING: PENSEL

- Synthetic brushes for water-based paints.
- 15% water when used as a primer

PÅFØRING OG FORTYNDING: RULLE

- 20 mm textured polyamide rolls or long-haired brushes according to the roughness of the surface
- 15% water when used as a primer

RENGØRING AF Udstyr/SPILD

water

SIKKERHEDSDATA

| | |
|----------------------------|---|
| VOC-niveau: | 139 g/l max. |
| VOC-kategori: | A/i |
| VOC-grænse: | 140 g/l (2010) |
| Bemærkninger om sikkerhed: | Consult the relevant product safety sheet and the information on the packaging. |

HOLDBARHED

Minimum of 2 years from production date in unopened, original packaging, if stored in dry, well-ventilated areas, not in full sun, at temperatures between 5 ° and 35 ° C.

Udstedelsesdato: 28/11/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu