



MURPRIM S

Solvent-based primer with high covering power



- Based on Pliolite
- Impregnates & fixes the mineral substrate
- To be applied on slightly damp surfaces
- Good coverage
- Applicable to recently plastered walls

MURPRIM S

DESCRIPTION

Solvent-based primer for use in combination with all Mathys façade paints

RECOMMENDED USE

Solvent based fixing primer for mineral substrates, old and sound substrates that can be covered with Murfill RP Siloxan, Murfill WP , and for elastic joint filler: Elastofill and Murfiller.

RECOMMENDED SYSTEM

Bare substrate or well conserved undercoats: Murprim Aqua + 400 g/m² MURFILL RP Siloxan or Murfill WP. Old well conserved undercoats must be compatible. Check substrate in advance. Surface irregularities Levelling with repair mortar (Pegacrete) or with filler.

TECHNICAL DATA

Density (g/cm ³):	± 1,16
Solids content in volume:	± 27 %
Water Vapour Permeability:	Sd= 0,0031 m (20 µm DFT)

THEORETICAL CONSUMPTION

110 g/m²

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrate must be completely clean, dry and sound and insensitive to water. In case of contamination by micro-organisms the substrate must first be cleaned with a fungicide solution. If the substrate is oily and dirty, this must be cleaned with a solution of Cleaner/degreaser ND14. Remove old not adhering coats.

DIRECTIONS FOR USE

To ensure homogeneity coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

Minimum temperature 5°C, maximum temperature 35°C and maximum relative humidity 80 %. No condensation during drying time .Low temperatures and/or high relative humidity will extend the drying time.

APPLICATION & THINNING: BRUSH

Natural silk and polyamide.

20 Vol.%white spirit

APPLICATION & THINNING: ROLLER

12 mm or long haired brushes according to roughness of substrate.

20 Vol.% white spirit

CLEANING OF EQUIPMENT / SPILLS

White spirit or Thinner Rust Oleum 160

SAFETY DATA

VOC level:	749 g/l max
VOC category:	A/h
VOC limit:	750 g/l (2010)
Remarks regarding safety:	Consult safety data sheet and Safety information printed on the can.

SHELF LIFE

Minimum of 2 years from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Date issued: 03/04/2025

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu