



Quality Paints since 1845
MATHYS®



PARACEM® DECO PLAFOND

One-coat ceiling paint

- Exceptional high covering power (covers mostly in 1 layer)
- Uniform matt finish without laps
- Delayed drying (enables to paint large surfaces)
- Odourless
- Extra matt

PARACEM® DECO PLAFOND

BESKRIVELSE

Paracem Deco Plafond is a super covering and extra matt acrylic paint for ceilings and inner walls. Applicable on most mineral substrates.

ANBEFALET BRUG

For indoor walls and ceilings: on plaster, plasterboard, rendering, bricks, concrete, etc. as well as on old paints, wallpaper, ingrain wallpaper, etc.

TEKNISK DATA

Tæthed:	1,41 - 1,45
Glansgrad:	Mat
Glansgrad ved 60°:	Matt: 2%
Faststofindhold i vægt:	52 - 54%
Tørstofindhold i volumen:	32 - 34%

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringsstør:	2 hours
Genbehandlingstør:	4 hours
Fuldt hærdet:	1 day

ANBEFALET VÅDFILMTYKKELSE

140 µm

ANBEFALET TØRFILMTYKKELSE

45 µm

TEORETISK FORBRUG

6 - 8 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity, roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Soft Plafond directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous. You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

Minimum 5°C / Maximum 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Apply undiluted.

PÅFØRING OG FORTYNDING: RULLE

Apply undiluted.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

If necessary, dilute with some water.

Nozzle: 011 - 013 / Pressure: 200 bars, dilute with maximum 3% volume water.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

Not recommended.

RENGØRING AF UDSTYR/SPILD

Water.

SIKKERHEDSDATA

VOC-niveau:	28 g/l
VOC-færdigblanding:	29 g/l
VOC-kategori:	A/a
VOC-grænse:	30 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production when kept in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 25/09/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu