



Quality Paints since 1845
MATHYS®



PARACEM® DECO ULTRA CLEAN

Washable interior wall paint with a matt finish

- Excellent cleanability
- Excellent mechanical resistance against rubbing
- Low dirt pick up
- Easy to apply
- Excellent flow

PARACEM® DECO ULTRA CLEAN

BESKRIVELSE

Paracem® Deco Ultra Clean is a washable waterborne acrylic interior wall paint with a matt finish. This decorative paint is available in white and in almost every colour, from light to dark tints.

ANBEFALET BRUG

Ideal finish for the walls of interior rooms that require regular cleaning (e.g. children's rooms, kitchens,...). Suitable for use on most substrates (plaster, bricks, concrete, etc.) in private and in public buildings.

TEKNISK DATA

Tæthed:	1,36 - 1,40 (white - wit - blanc)
Glansgrad:	Mat
Glansgrad ved 60°:	Matt: 1-2%
Glansgrad ved 85°:	Matt: 2,5-3,5%
Faststofindhold i vægt:	60,5 - 62,5% (white)
Tørstofindhold i volumen:	49 - 51% (white)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	30 minutes
Genbehandlingstør:	1 hour
Fuldt hærdet:	7 days

ANBEFALET VÅDFILMTYKKELSE

100 µm

ANBEFALET TØRFILMTYKKELSE

50 µm

TEORETISK FORBRUG

7 - 10 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

The surface must be dry and free of dust and grease.

You can paint Paracem® Deco Ultra Clean directly over clean, old layers of paint that are still in good condition and onto surfaces that are not too porous.

You must treat porous surfaces with Paracem® Deco Primer first.

Highly porous surfaces, smooth plaster, and water-resistant plasterboard must be impregnated with Pegafix first.

Nicotine and water stains must be isolated first with Pegamat® RL or Zinsser primers Bulls Eye 123 or 123 Plus.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim Aqua or Zinsser primers Bulls Eye 123 or 123 Plus).

Metal objects without rust spots are to be pre-treated with Pegalink®, or Zinsser primers Bulls Eye 123.

On glass fibre, apply preferably first a coat of Paracem® Deco Primer or Zinsser primers Bulls Eye 123 or 123 Plus before finishing with 2 coats of Paracem® Deco Ultra Clean.

When working in combination with a joint sealant, we recommend using our acrylic sealant Elastopro, which can be painted over after drying for at least 1 hour (20°C, 60% r.h.).

BRUGSANVISNING

To ensure homogeneity, thoroughly stir prior to use. Apply two layers of Paracem Deco Ultra Clean. For best result use a brush with synthetic bristles or a 10 mm micro fiber roller.

ANVENDELSESBETINGELSER

> 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Apply undiluted with brush with synthetic bristles.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Nozzle: 013 - 019 / Pressure: 160 - 200 bars.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

not recommended.

RENGØRING AF UDSTYR/SPILD

Clean tools with water, dispose of residue in the appropriate manner.

BEMÆRKNINGER

Cleaning instructions: Remove the contamination as soon as possible. Most contamination can easily be removed with a soft, damp cloth. Use lukewarm water and a mild colourless detergent. Do not use abrasive cleaning products. Do not use excessive pressure when cleaning as this may result in removing paint which will leave marks.

For more serious contaminations first wipe the substrate with a soft damp cloth, then use Mathys Multi-cleaner (diluted 1:100). Allow to dry.

The best cleaning results are achieved after the Paracem® Deco Ultra Clean has dried for minimum 7 days.

Although extensive evaluations have been undertaken to ensure the cleanability of the Paracem® Deco Ultra Clean it might be possible that some contamination is difficult to remove and leaves traces.

Touching the paint may leave marks this is due to the matt nature of the product (the marks will be more visible on dark colours).

SIKKERHEDSDATA

VOC-niveau:	15 g/l
VOC-færdigblanding:	15 g/l
VOC-kategori:	A/a
VOC-grænse:	30 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 31/10/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu