



## PARACEM® SEMI-MATT

# Acrylic exterior wall paint with high covering power



- High durability
- Perfect saponification resistance
- Particularly high covering capacity
- Sufficiently breathing (water vapour permeable)
- Hardly permeable to rain Excellent weather resistance

# PARACEM® SEMI-MATT

## DESCRIPTION

- Acrylic exterior wall paint with high covering power
- Acrylic paint for outside and inside use

## RECOMMENDED USE

For old or new substrates like masonry, cement rendering or plaster, concrete, tiles, plaster boards and wooden panels.

## TECHNICAL DATA

Density (g/cm³):	1,5
Gloss Level:	Semi-Matt
Gloss level at 60°:	5%
Solids Content in weight:	64%
Solids content in volume:	46%
Water Vapour Permeability:	23g/m²/24h and Sd (m) = 1,0

## DRY TIMES BY 20° C/RH 50%

Touch dry:	40 minutes (10 m²/l)
Dry to handle:	2 hours (10 m²/l)
Dry to recoat:	4 hours (10 m²/l)
Fully cured:	1 day

## RECOMMENDED WET FILM THICKNESS

100 micron (cons.: 10 m²/l)

## RECOMMENDED DRY FILM THICKNESS

45 micron (cons.: 10 m²/l)

## THEORETICAL CONSUMPTION

7 - 10 m²/l per coat

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

The substrate must be sufficiently dry and stable; clean thoroughly.  
In case of fungal growth: treat first with an adequate moss-preventing product. On porous substrates apply first a coat of Parafix or Pegafix / Paracem (25 / 75). On very smooth bricks, apply a first coat of Noxyde diluted with 25% water, or a coat of Pegalink. Impregnate old chalking paints, after cleaning, with a coat of Fixonal or Pegafix.  
For stain, graffiti blocking and/or very fast recoating on all substrates, for interior or exterior, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.  
Fill up holes and seal joints or fissures with Elastofill. If necessary, fill with Pegaflex. Flat down and remove dust. Hereafter, apply 1 - 2 coats of Paracem.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Minimum 5C / Maximum 80 % R.H.

## APPLICATION & THINNING: BRUSH

Apply with flat brush

## APPLICATION & THINNING: ROLLER

Apply with dispersion roller.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 013 - 018 / Pressure: 180 bars.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Dilute with water (3 - 5% volume).

## CLEANING OF EQUIPMENT / SPILLS

Water.

## SAFETY DATA

VOC level:	25 g/l max.
VOC category:	A/c
VOC limit:	75 g/l (2007) / 40 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 23/10/2023

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)