Quality Paints since 1845

MATHYS®

PARACEM® UNIVERSAL

Excellent covering universal paint for all outside work

- Matt universal paint for the outdoors
- Usable on all surfaces, such as bricks, gutters, wood, aluminium, etc.
- Colour and weatherproof for long-term protection
- Protection of the dried coat against contamination by mould
- Primer and finishing coat in one

WWW.MATHYSPAINTS.EU

PARACEM® UNIVERSAL

ОПИСАНИЕ
Excellent covering universal paint for outside work. Extremely suitable for durable decoration of woodwork, metal, bricks, plastic, concrete and more. New or already painted. Paracem® Universal is water-vapour permeable, water repellent, and requires minimum maintenance. Self-priming in most cases. Protects dry coating against contamination by mould. Paracem® Universal has a unique property, namely, the colour does not darken when the façade is wet.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА
Developed for all outside work, Paracem® Universal is ideal for applying to bricks, façade cladding, plaster, woodwork, plastic, galvanised metal, steel, concrete, and more. Paracem® Universal is self-priming and will immediately adhere to existing glossy surfaces without the need for sanding. A separate primer is unnecessary for most applications. Paracem® Universal provides excellent resistance against cracking, blistering, flaking, rain, and severe weather conditions.
Two-layer system: Apply the first layer, which primes and seals the surface. The second layer completes the sealing process and provides additional moisture resistance and protection.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,25
Гланцово ниво:	Мат
Гланцово ниво при 60º:	± 2%
gloss_level_85:	± 3%
Съдържание на сухо вещество (по тегло):	40%
Съдържание на сухо вещество (по обем):	40%
water_vapour_permeability:	Sd = 0,41 m

ВРЕМЕ ЗА СУШЕНЕ ДО 20º C/RH 50%

Сух на допир:	1 h
Сух за употреба:	1 h
Готов за повторно нанасяне:	1 h
group_dry_40_full_cure:	7 days

МОКЪР СЛОЙ
100 µm per coat

СУХ СЛОЙ
40 µm per coat

РАЗХОДНА НОРМА
8-12 m²/l/coat

КОНСУМАЦИЯ
Practical coverage depends on many factors such as porosity and roughness of the substrate. A normal application consists of two layers. Apply an extra layer to areas with high exposure such as window sills and eaves.

ПОДГОТОВКА НА ПОВЪРХНОСТТА
The surface must be clean, dry and free of dust, dirt, grease, oil, wax, mould, glue residues, etc. Remove old non-adhering layers of paint. Clean the surface using ND14. Use AMW concentrate to remove algae and mould.

НАЧИН НА УПОТРЕБА
Mix carefully before use.

УСЛОВИЯ ЗА НАНАСЯНЕ
> 10°C, < 85% R.H.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА
Apply with brush with synthetic bristles.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК
Apply with synthetic roller.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)
Nozzle: 0.017 / Pressure: 140 - 170 bar

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ
Use lukewarm soapy water to clean off stains and materials.

ЗАБЕЛЕЖКИ
Paracem® Universal is not recommended for use on floors, terraces, or horizontal surfaces that may be drenched in water or exposed to water for a long period of time. Before applying Paracem® Universal, we recommend that you thoroughly sand and degrease unweathered/new powder coatings and similar surfaces. Not suitable for application onto new plastisol or a new powder coating. These surfaces must be fully weathered.
Paracem® Universal has no anti corrosive properties, so don't apply directly on ferrous metal surfaces, but always use an appropriate anticorrosive primer like Metal Cladding Primer.
Specific substrates like enamelled bricks require an adhesion coat with diluted Noxyde.

ДАННИ ЗА БЕЗОПАСНОСТ

Ниво на ЛОС:	35 g/l
Готов за употреба ЛОС (VOC Readymix):	35 g/l
Категория ЛОС:	IIA/d
group_voc_40_limit:	130g/l (2010.)
Забележки относно безопасността:	Consult Safety Data Sheet and Safety Information printed on the can.

СРОК НА ГОДНОСТ
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5 and 35°C.

Дата на издаване: 22/06/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu