Quality Paints since 1845
MATHYS®

PARAFIX®

Fixating and impregnating primer

- Parafix® is a special impregnating primer for roofing and bituminous products, before recoating with Dacfill
- It is also used as a primer under Paracem®.
- Parafix® is a milky liquid which becomes colourless after drying
- It prevents the absorption of waterborne paints on porous substrates

PARAFIX®

DESCRIPTION
Colourless fixation primer based on acrylic dispersions for weathered bituminous substrates. It prevents the absorption of waterborne paints on porous substrates.

RECOMMENDED USE
Fixation coat on weathered bituminous surfaces before recoating with Dacfill, Dacfill HZ or Dac-Hydro-Alu.

TECHNICAL DATA

Density (g/cm³):	1,0
Gloss Level:	Gloss
Gloss level at 60º:	Glossy: 90%
Solids Content in weight:	27 - 29%
Solids content in volume:	27 - 29 %

DRY TIMES BY 20º C/RH 50%

Touch dry:	1,5 hours
Dry to handle:	4 hours
Dry to recoat:	1 day
Fully cured:	1 week

RECOMMENDED WET FILM THICKNESS
100 µm

RECOMMENDED DRY FILM THICKNESS
28 µm

THEORETICAL CONSUMPTION
5 - 10 m²/l

PRACTICAL CONSUMPTION
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION
Do not apply on fibre cement boards: use Primer 44 HS in this case.
Do not apply on low porous substrates like plaster, use Pegafix in this case.

DIRECTIONS FOR USE
To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS
> 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH
Apply undiluted.

APPLICATION & THINNING: ROLLER
Apply undiluted.

APPLICATION & THINNING: AIRLESS SPRAY
Apply undiluted.
Nozzle: 011 - 015 / Pressure: 180 - 200 bars

APPLICATION & THINNING: AIR-ATOMISED SPRAY
Dilute with water.

CLEANING OF EQUIPMENT / SPILLS
Water.

SAFETY DATA

VOC level:	40 g/l
VOC readymix:	40 g/l
VOC category:	A/i
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 22/06/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu