Quality Paints since 1845
MATHYS®

PARASIL COMPACT

High build intermediate coat, siloxane resins

- Waterborne acrylic and polysiloxane resin
- Very thick coat with high covering power
- Application in 1 or 2 coats
- Direct application on well adhering, solid, even and uneven substrates
- Masks haircracking

PARASIL COMPACT

DESCRIPTION
High build priming and intermediate coat based on waterborne acrylic and polysiloxane resins. To be used in combination with ParaSil®.

RECOMMENDED USE
High build priming and intermediate coat for the protection and decoration of new or old exterior walls. Walls in masonry, concrete, hydraulic plasters. Masks hair-line cracking. Maintenance of old elastic paint coats and outer wall insulation.

RECOMMENDED SYSTEM
On bare substrates or old well adhering and compatible undercoats: 1 coat of Parasil Compact: 500 to 700 g/m² plus 1 or 2 top coats of Parasil.
On very porous substrates: pretreatment with Primer 44 HS – 10 m²/l. Irregular surfaces: levelling with Pegacrete or with a suitable filler.

TECHNICAL DATA

Density (g/cm³):	1,54
Gloss Level:	Matt
Solids Content in weight:	67 - 69 %
Solids content in volume:	49 - 51 %

DRY TIMES BY 20º C/RH 50%

Touch dry:	4 hours
Dry to recoat:	24 hours

PRACTICAL CONSUMPTION

SURFACE PREPARATION
The substrate must be completely clean, dry and solid. In case of contamination by microorganisms the substrate must first be cleaned with a fungicide solution.

DIRECTIONS FOR USE
To ensure homogeneity coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS
The works must be performed in conformity with DTU 59-1. Minimum temperature 7°C, maximum 30 °C and maximum relative humidity 80%.
No condensation during drying time. Low temperatures and/or high relative humidity willextend the drying time. Do not apply on hot walls and in direct sunlight.

APPLICATION & THINNING: BRUSH
Synthetic brushes for water dilutable paints

APPLICATION & THINNING: ROLLER
Polyamide rollers with 20 mm long hair or longer according to roughness.

CLEANING OF EQUIPMENT / SPILLS
Water.

SAFETY DATA

VOC level:	35 g/l
VOC readymix:	35 g/l
VOC category:	A/c
VOC limit:	40 g/l
Remarks regarding safety:	Consult safety data sheet and Safety information printed on the can.

SHELF LIFE
Minimum of 1 year from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 7° and 30°C.

Date issued: 22/06/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu