



PARASIL

A high build matt silanized wall paint

- Mineral-like matt aspect
- Durable
- Low odour
- Dirt and water repellent
- Low stress

PARASIL

BESKRIVELSE

ParaSil® is a high build matt silanized wall paint. Based on siloxane resins and 100% acrylic resins. Suitable for uneven, structured substrates.

ANBEFALET BRUG

Mineral matt finish for exterior walls. Can be applied on most mineral substrates and old dispersion paints. Suitable for uneven structured substrates. No cracking in deeper areas of the treated substrate (e.g. brick).

TEKNISK DATA

Tæthed:	1,47 - 1,51 (wit)
Glansgrad:	Mat
Faststofindhold i vægt:	68,5 - 70,5 % (wit)
Tørstofindhold i volumen:	52,5 - 54,5 % (wit)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	2-3 hours
Genbehandlingstør:	12 hours
Fuldt hærdet:	1 day

TEORETISK FORBRUG

5 - 7 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application (see DIN 53220).

FORBEHANDLING AF OVERFLADEN

Old cleaned layers in good condition and light porous substrates (such as concrete, cement, plaster, etc.) can be recoated directly with ParaSil. Stongly porous substrates and smooth plaster must first be impregnated with a coat of Pegafix Color EXT.

BRUGSANVISNING

Substrate must be sufficiently dry and stable, and well cleaned. Previously cleaned old coatings in good condition and slightly porous and homogeneous substrates can be directly coated with Parasil or with high filling undercoat Parasil Compact in case of uneven surfer. Very porous substrates or smooth renderings or water resistant plasters will be previously impregnated with Pegaprim Exterior. To block stains, graffiti and/or very fast recoating on any substrate, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain.

ANVENDELSESBETINGELSER

> 10°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Do not dilute.

PÅFØRING OG FORTYNDING: RULLE

Do not dilute.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Nozzle: 013 - 019 / Pressure: 160 - 200 bar.

RENGØRING AF Udstyr/SPILD

Water.

SIKKERHEDSDATA

VOC-niveau:	23 g/l
VOC-færdigblanding:	23 g/l
VOC-kategori:	IIA/c
VOC-grænse:	40 g/l
Bemærkninger om sikkerhed:	Consult safety data sheet and Safety information printed on the can.

HOLDBARHED

At least 1 year from date of production in unopened original cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 7° and 30°C.

Udstedelsesdato: 20/12/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu