

Quality Paints since 1845
MATHYS[®]



PEGAFIX[®] UNIVERSAL

Colourless impregnating primer

High fixing capacity.

WWW.MATHYSPAINTS.EU

PEGAFIX® UNIVERSAL

BESKRIVELSE

Colourless impregnating primer based on acrylic hydrosols.

ANBEFALT BRUK

On different porous and chalking substrates, before painting them with waterborne paints.

TEKNISKE DATA

Tetthet:	1,0
Glansgrad:	Blank
Glansgrad ved 60°:	Glossy: > 80%
Tørrestoffinnhold i vekt:	14 - 16 %
Tørrestoffinnhold i volum:	14 - 16 %

TØRKETID VED 20°C/50% RELATIV LUFTFUKTIGHET

Støtør:	1 hour
Håndterbar:	4 hours
Overmalbar:	2-4 hours
Herdetid:	24 hours

ANBEFALT VÅTFILMTYKKELSE

100 µm

ANBEFALT TØRRFILMTYKKELSE

15 µm

TEORETISK FORBRUK

Very porous substrates (concrete, bricks): 5 - 10 m²/l

Little porous substrates (plaster, porous paints for inside use): 15 - 20 m²/l

PRAKTISK FORBRUK

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

KLARGJØRING AV OVERFLATE

Remove dust and / or clean carefully.

Blistering plaster has to be sanded slightly to ensure a good adhesion or an adhesion test has to be done in advance.

BRUKSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

PÅFØRINGSBETINGELSER

> 5°C, < 90% R.H.

PÅFØRING & FORTYNNING: PENSEL

Apply undiluted.

PÅFØRING & FORTYNNING: RULLE

Apply undiluted.

PÅFØRING & FORTYNNING: LUFTFRI SPRØYTE

Nozzle: 11 - 15 / Pressure: 200 bars.

Apply undiluted.

PÅFØRING & FORTYNNING: FORSTØVNINGS-SPRØYTE

Apply undiluted.

RENGJØRING AV UTSTYR/SPILL

Water.

MERKNADER

On low porosity substrates, Pegafix is preferred above Parafix and Porisol because of its better penetration characteristics.

Possible dried spots (on windows, floors, etc.) can be removed with Thinner 22.

When using on chalking substrates, always test for fixing suitability.

SIKKERHETSDATA

VOC nivå:	0 g/l
VOC ferdigblandet:	0 g/l
VOC kategori:	A/g
VOC grense:	30 g/l
Merknader angående sikkerhet:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHET

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Utstedt dato: 07/02/2025

Tilgjengelige farger & størrelse på forpakninger: Vennligst referer til den respektive produktsiden på www.rust-oleum.eu for en oversikt over tilgjengelige farger og størrelse på forpakninger.

Ansvarsfraskrivelse: Så langt vi kjenner til er informasjonen i dette dokumentet korrekt og nøyaktig. Den er gitt i god tro, men uten garanti. Brukeren må selv avgjøre om våre produkter er egnet for hans/hennes bestemte formål. Ikke under noen omstendigheter skal Rust-Oleum Europe bli gjort ansvarlig for indirekte eller tilfældige skader. Produktene må lagres, håndteres og påføres under forhold som tilfredsstiller Rust-Oleum Europes anbefalinger som er detaljert beskrevet i den siste oppdaterte kopien av produktdatabladet. Brukerne er selv ansvarlige for at de har den siste oppdaterte kopien. De siste oppdaterte kopier av produktdatabladet er tilgjengelig, og kan lastes ned gratis fra www.rust-oleum.eu, eller de kan fås ved forespørsel til vår kundeserviceavdeling. Rust-Oleum Europe forbeholder seg retten til å endre egenskapene til produktene sine uten forhåndsvarsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu