



## **PEGAFLEX®**

---

### **Levelling filler based on acrylic resins dispersed in water**

- High flexibility and elasticity
- Excellent adhesion on all sound substrates and paints
- Perfect alkali resistant
- Not affected by ageing thus keeping its original flexibility
- Sufficiently hard, but can still be sanded easily

## BESKRIVELSE

Levelling filler based on acrylic resins dispersed in water.

## ANBEFALET BRUG

For indoor and outdoor works; can be used on any non-powdering substrates.

## TEKNISK DATA

|                           |           |
|---------------------------|-----------|
| Tæthed:                   | ± 1,8     |
| Glansgrad:                | Mat       |
| Glansgrad ved 60°:        | Matt: 3%  |
| Faststofindhold i vægt:   | 78 - 80 % |
| Tørstofindhold i volumen: | 61 - 64 % |

## TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

|                    |          |
|--------------------|----------|
| Berøringstør:      | 3 hours  |
| Håndteringstør:    | 8 hours  |
| Genbehandlingstør: | 24 hours |
| Fuldt hærdet:      | 2 days   |

## ANBEFALET VÅDFILMTYKKELSE

1000 µm

## ANBEFALET TØRFILMTYKKELSE

630 µm

## TEORETISK FORBRUG

Max. 1,8 kg/m² (= 1 mm thick)

## PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## FORBEHANDLING AF OVERFLADEN

Fill up deep holes with a filler or with a repair mortar (Pegacrete).

Chalking substrates must be primed with Fixonal.

Porous mineral substrates have to be pre-treated with Pegafix.

Bare wood should be impregnated with Adex first.

If you want to recoat with an acrylic paint, you should isolate the filled up parts with Porisol first. If it is necessary to get a thick layer, you should apply several layers after hardening of the previous layer.

## BRUGSANVISNING

Use a filling knife and apply thin layers.

## ANVENDELSESBETINGELSER

> 5°C, < 80% R.H.

## RENGØRING AF UDSTYR/SPILD

With water as long as Pegaflex has not dried; when dry clean with Thinner 22.

## BEMÆRKNINGER

Pegaflex can easily be sanded wet, but not dry.

## SIKKERHEDSDATA

|                            |                                                                      |
|----------------------------|----------------------------------------------------------------------|
| VOC-niveau:                | 30 g/l                                                               |
| VOC-færdigblanding:        | 30 g/l                                                               |
| VOC-kategori:              | A/i                                                                  |
| VOC-grænse:                | 140 g/l                                                              |
| Bemærkninger om sikkerhed: | Consult Safety Data Sheet and Safety Information printed on the can. |

## HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 07/02/2025

**Tilgængelige farver og pakningsstørrelser:** Der henvises til den respektive produktside på [www.rust-oleum.eu](http://www.rust-oleum.eu) for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

**Ansvarsfraskrivelse:** Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europas anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra [www.rust-oleum.eu](http://www.rust-oleum.eu) eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)