



Quality Paints since 1845
MATHYS[®]



PEGAMAT[®] AQUA ISOLE

Low tension stain blocking renovation paint

- Low tension film
- Primer and topcoat in one
- Insulates nicotine and smoke stains, old damp spots and numerous colorants
- Long open time
- Quickly recoatable

PEGAMAT® AQUA ISOLE

BESKRIVELSE

Water based low tension matt renovation and stain blocking paint for use on interior walls and ceilings based on modified alkylid resins.

ANBEFALET BRUG

Low tension renovation paint for interior walls and ceilings.

TEKNISK DATA

Tæthed:	1,45 - 1,51
Glansgrad:	Mat
Glansgrad ved 85°:	Matt: 2%
Faststofindhold i vægt:	58 - 62 % (weiss)
Tørstofindhold i volumen:	38 - 42 % (weiss)

TØRRETIDER VED 20°C/50% RELATIV LUFTFUGTIGHED

Berøringstør:	1 hour
Genbehandlingstør:	2 hour
Fuldt hærdet:	2 days

ANBEFALET VÅDFILMYKKELSE

140 µm

ANBEFALET TØRFILMYKKELSE

56 µm

TEORETISK FORBRUG

7 m²/l per coat

PRAKTISK FORBRUG

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

FORBEHANDLING AF OVERFLADEN

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc.

Apply on a dry and sound substrate. Apply 1 or 2 coats according to the condition of the substrate.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat Aqua Isole.

On very absorbent substrates (not painted), apply an impregnation coat of Pegafix.

On substrates with nicotine spots: first clean these with an ammonia solution in order to receive a better efficiency of the paint.

Can be applied on completely dry Elastofill/Pegaflex without the risk of crack formation.

BRUGSANVISNING

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

ANVENDELSESBETINGELSER

> 5°C, < 80% R.H.

PÅFØRING OG FORTYNDING: PENSEL

Apply undiluted.

PÅFØRING OG FORTYNDING: RULLE

Apply undiluted.

PÅFØRING OG FORTYNDING: LUFTLØS SPRØJTE

Nozzle: 011 - 013 / Pressure: 180 bar.

If necessary, dilute with a little water.

PÅFØRING OG FORTYNDING: LUFTATOMISERET SPRØJTE

If necessary, dilute with a little water.

RENGØRING AF UDSKYR/SPILD

Water.

BEMÆRKNINGER

Apply a preliminary test patch in case of old damp spots and colour marks. When insulation properties are insufficient, use Pegamat RL Isole or Pegaprim Isofix.

Can be applied directly on Pegamat RL Isole, Pegaprim Isofix and Pegaprim Xpress.

Can be recoated with all water-based paint, and also with Pegamat RL Isole.

SIKKERHEDSDATA

VOC-niveau:	53 g/l
VOC-færdigblanding:	53 g/l
VOC-kategori:	A/i
VOC-grænse:	140 g/l
Bemærkninger om sikkerhed:	Consult Safety Data Sheet and Safety Information printed on the can.

HOLDBARHED

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Udstedelsesdato: 07/06/2024

Tilgængelige farver og pakningsstørrelser: Der henvises til den respektive produktside på www.rust-oleum.eu for en oversigt over aktuelle tilgængelige farver og pakningsstørrelser.

Ansvarsfraskrivelse: Oplysningerne heri er efter vores bedste overbevisning korrekte, og er afgivet i god tro, men uden garanti. Brugeren vil blive anset for at selvstændigt at have bekræftet egnetheden af vores produkter til hans/hendes egen særlige formål. Rust-Oleum Europa kan under ingen omstændigheder holdes ansvarlig for følgeskader eller hændelige skader. Produkterne skal opbevares, håndteres og anvendes under forhold, der er i overensstemmelse med Rust-Oleum Europes anbefalinger beskrevet i den nyeste udgave af databladet. Det er brugernes ansvar at sikre, at de har den opdaterede udgave. De nyeste udgaver af datablade kan downloades gratis fra www.rust-oleum.eu eller tilsendes på anmodning til vores kundeservice. Rust-Oleum Europe forbeholder sig ret til at ændre egenskaberne for sine produkter uden forudgående varsel.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu