



## PEGAMAT® RL ISOLE

# Low tension renovation and stain blocking paint

- Good covering power
- Low odour
- Non yellowing
- Low tension film
- Unsaponifiable

# PEGAMAT® RL ISOLE

## POPIS PRODUKTU (DLOUHÝ)

Deodorised low tension solvent-based insulating or blocking paint based on plastified acrylic resins.

## DOPORUČENÉ POUŽITÍ

Low tension renovation paint for interior walls and ceilings.

## TECHNICAL\_DATA

Hustota (g/cm <sup>3</sup> ):	1.33 - 1.37 g/cm <sup>3</sup>
Úroveň lesku:	Matt
Úroveň lesku při 60°:	Matt: < 2%
Obsah pevných látek v hmotnosti:	64 - 66%
Obsah pevných látek v objemu:	38 - 40%

## DRY\_TIMES\_BY\_20

Dotykem suché:	3 h
Suchý nátěr:	Wet in wet or after 4 h
Plně vytvrzené:	1 day

## DOPORUČENÁ TLOUŠŤKA MOKRÉHO FILMU

100 µm

## DOPORUČENÁ TLOUŠŤKA SUCHÉHO FILMU

40 µm

## TEORETICKÁ SPOTŘEBA

9 - 12 m<sup>2</sup>/l per coat

## PRAKTICKÁ SPOTŘEBA

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## PŘÍPRAVA POVRCHU

Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Substrates should be sufficiently dry and stable. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.

Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat RL Isole.

Very porous substrates are to be impregnated first with Pegafix.

Persistent stains are to be treated with Pegaprim® Isofix.

## NÁVOD K POUŽITÍ

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## PODMÍNKY POUŽITÍ

Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

## APLIKACE A ŘEDĚNÍ: ŠTĚTEC

Dilute with 3-5% Thinner RL or White spirit if necessary.

## APLIKACE A ŘEDĚNÍ: VÁLEČEK

Dilute with 3-5% Thinner RL or White spirit if necessary.

## APLIKACE A ŘEDĚNÍ: BEZVZDUCHOVÝ SPREJ

Nozzle: 011 - 015 / Pressure: 180 bars.

Dilute max. 5% with Thinner RL or White spirit if necessary.

## APLIKACE A ŘEDĚNÍ: VZDUCHOVÝ ATOMIZOVANÝ SPREJ

Possible.

## ČIŠTĚNÍ ZAŘÍZENÍ / ROZLITÍ

White spirit.

## POZNÁMKY

White spirit increases the odour and makes its use impossible on polystyrene foam. Pegamat RL Isole is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat RL Isole can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine.

## DATA\_SAFETY\_DATA

Úroveň těkavých organických

látek: 455 g/l

VOC readymix: 485 g/l

Kategorie VOC: A/i

Limitní hodnota VOC: 500 g/l

Poznámky k bezpečnosti: Consult Safety Data Sheet and Safety Information printed on the can.

## DOBA POUŽITELNOSTI

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

last\_updated: 07/02/2025

footer\_data\_colors\_pack\_sizes: footer\_data\_colors\_pack\_sizes.value

footer\_data\_disclaimer: footer\_data\_disclaimer.value

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu