Quality Paints since 1845
MATHYS®

PEGAMAT® RL ISOLE

Low tension renovation and stain blocking paint

- Good covering power
- Low odour
- Non yellowing
- Low tension film
- Unsaponifiable

PEGAMAT® RL ISOLE

DESCRIPTION
Deodorised low tension solvent-based insulating or blocking paint based on plastified acrylic resins.

RECOMMENDED USE
Low tension renovation paint for interior walls and ceilings.

TECHNICAL DATA

Density (g/cm³):	1.33 - 1.37 g/cm³
Gloss Level:	Matt
Gloss level at 60º:	Matt: < 2%
Solids Content in weight:	64 - 66%
Solids content in volume:	38 - 40%

DRY TIMES BY 20º C/RH 50%

Touch dry:	3 h
Dry to recoat:	Wet in wet or after 4 h
Fully cured:	1 day

RECOMMENDED WET FILM THICKNESS
100 µm

RECOMMENDED DRY FILM THICKNESS
40 µm

THEORETICAL CONSUMPTION
9 - 12 m²/l per coat

PRACTICAL CONSUMPTION
Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION
Suitable substrates are: plaster, cement, concrete, fibreboard, insulating hard foam boards, old paints, wallpaper, etc. Substrates should be sufficiently dry and stable. Apply 1 or 2 coats according to the condition of the substrate; if necessary, the second coat can be applied wet in wet. Do not apply on Elastofill; when using Pegaflex, it must first be insulated with Porisol.
Old cleaned layers in good condition and light porous substrates may be recoated directly with Pegamat RL Isole.
Very porous substrates are to be impregnated first with Pegafix.
Persistent stains are to be treated with Pegaprim® Isofix.

DIRECTIONS FOR USE
To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS
Apply in a dry and well-ventilated area. > 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH
Dilute with 3-5% Thinner RL or White spirit if necessary.

APPLICATION & THINNING: ROLLER
Dilute with 3-5% Thinner RL or White spirit if necessary.

APPLICATION & THINNING: AIRLESS SPRAY
Nozzle: 011 - 015 / Pressure: 180 bars.
Dilute max. 5% with Thinner RL or White spirit if necessary.

APPLICATION & THINNING: AIR-ATOMISED SPRAY
Possible.

CLEANING OF EQUIPMENT / SPILLS
White spirit.

REMARKS
White spirit increases the odour and makes its use impossible on polystyrene foam. Pegamat RL Isole is a reversible paint system, this means that it dissolves in its own solvent. Therefore, dried spots of Pegamat RL Isole can be removed with Thinner RL or white spirit. Do not tint with universal pigments or on the tinting machine.

SAFETY DATA

VOC level:	455 g/l
VOC readymix:	485 g/l
VOC category:	A/i
VOC limit:	500 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE
Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 22/06/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu